



**BUREAU VERITAS** MINERAL LABORATORIES  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.  
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada  
PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

Submitted By: Greg Dawson  
Receiving Lab: Canada-Whitehorse  
Received: July 03, 2018  
Report Date: July 26, 2018  
Page: 1 of 4

## CERTIFICATE OF ANALYSIS

WHI18000213.1

### CLIENT JOB INFORMATION

Project: BZA  
Shipment ID: BZA-180610-10RAB  
P.O. Number  
Number of Samples: 69

### SAMPLE DISPOSAL

RTRN-PLP Return After 90 days  
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.  
Box 70  
Dawson Yukon Y0B 1G0  
Canada

CC: Jodie Gibson  
Ben McGrath  
Wes Hodson  
Isaac Fage

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

| Procedure Code | Number of Samples | Code Description                                    | Test Wgt (g) | Report Status | Lab |
|----------------|-------------------|---|--------------|---------------|-----|
| PRP70-250      | 67                | Crush, split and pulverize 250 g rock to 200 mesh   |              |               | WHI |
| SLBHP          | 2                 | Sort, label and box pulps                           |              |               | WHI |
| FA430          | 69                | Lead Collection Fire - Assay Fusion - AAS Finish    | 30           | Completed     | VAN |
| EN002          | 69                | Environmental disposal charge-Fire assay lead waste |              |               | VAN |
| AQ200          | 69                | 1:1:1 Aqua Regia digestion ICP-MS analysis          | 0.5          | Completed     | VAN |
| SHP01          | 69                | Per sample shipping charges for branch shipments    |              |               | VAN |

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.  
\*\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



**BUREAU VERITAS** MINERAL LABORATORIES  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method<br>Analyte<br>Unit<br>MDL | WGHT | FA430  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|
|         |                                  | Wgt  | Au     | Mo    | Cu    | Pb    | Zn    | Ag    | Ni    | Co    | Mn    | Fe    | As    | Au     | Th    | Sr    | Cd    | Sb    | Bi    | V     | Ca    |
|         |                                  | kg   | ppm    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppb    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     |
|         |                                  | 0.01 | 0.005  | 0.1   | 0.1   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 0.1   | 1     | 0.01  | 0.5    | 0.5   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     |
| 1694068 | Rab Sample                       | 4.04 | 0.025  | 1.0   | 7.6   | 26.3  | 37    | 0.2   | 5.0   | 1.9   | 114   | 0.87  | 78.9  | 13.3   | 12.4  | 8     | 0.2   | 0.8   | 0.1   | 6     | 0.05  |
| 1694069 | Rab Sample                       | 4.38 | 0.011  | 0.9   | 4.0   | 27.7  | 36    | 0.2   | 2.2   | 0.7   | 70    | 0.84  | 145.4 | 10.5   | 13.2  | 6     | 0.7   | 0.9   | <0.1  | <1    | 0.02  |
| 1694070 | Rab Sample                       | 2.21 | 0.010  | 0.8   | 4.9   | 25.7  | 37    | 0.2   | 0.7   | 0.7   | 111   | 0.69  | 125.1 | 7.5    | 13.2  | 5     | 0.4   | 0.7   | <0.1  | <1    | 0.02  |
| 1694071 | Rab Sample                       | 3.11 | 0.012  | 0.9   | 2.7   | 24.6  | 36    | 0.2   | 1.0   | 0.3   | 32    | 0.65  | 119.9 | 9.2    | 14.1  | 5     | 0.4   | 0.6   | 0.1   | <1    | 0.01  |
| 1694072 | Rab Sample                       | 3.31 | 0.028  | 0.6   | 3.1   | 21.2  | 42    | 0.2   | 0.8   | 0.2   | 34    | 0.69  | 156.4 | 22.9   | 12.8  | 8     | 0.5   | 1.2   | <0.1  | <1    | 0.02  |
| 1694073 | Rab Sample                       | 3.31 | 0.007  | 0.7   | 3.1   | 21.1  | 44    | 0.2   | 0.8   | 0.4   | 49    | 0.77  | 59.1  | 3.7    | 12.2  | 4     | 0.2   | 0.6   | <0.1  | <1    | 0.01  |
| 1694074 | Rab Sample                       | 3.61 | 0.010  | 0.7   | 2.8   | 31.5  | 58    | 0.2   | 0.9   | 0.5   | 51    | 0.68  | 105.6 | 8.6    | 12.0  | 4     | 0.5   | 0.6   | <0.1  | <1    | 0.01  |
| 1694075 | Rab Sample                       | 3.43 | 0.009  | 0.8   | 2.8   | 41.0  | 36    | 0.2   | 1.0   | 0.6   | 94    | 0.60  | 93.1  | 5.3    | 14.1  | 4     | 0.5   | 0.5   | <0.1  | <1    | 0.01  |
| 1694076 | Rab Sample                       | 3.42 | 0.008  | 0.8   | 2.6   | 24.3  | 27    | 0.2   | 0.9   | 0.3   | 46    | 0.54  | 78.0  | 4.7    | 11.7  | 3     | 0.6   | 0.7   | 0.1   | <1    | 0.01  |
| 1694077 | Rab Sample                       | 3.59 | 0.009  | 0.8   | 1.9   | 30.7  | 23    | 0.2   | 1.0   | 0.3   | 30    | 0.44  | 53.1  | 4.7    | 13.8  | 4     | 0.5   | 0.8   | 0.1   | <1    | 0.01  |
| 1694078 | Rab Sample                       | 3.45 | <0.005 | 0.7   | 2.7   | 19.7  | 34    | 0.2   | 1.0   | 0.3   | 32    | 0.47  | 15.9  | <0.5   | 13.0  | 5     | 0.2   | 0.3   | 0.1   | <1    | 0.02  |
| 1694079 | Rab Sample                       | 3.58 | 0.007  | 0.9   | 3.0   | 32.6  | 64    | 0.5   | 1.3   | 0.9   | 104   | 0.73  | 25.2  | 3.2    | 12.3  | 7     | 0.5   | 0.3   | 0.1   | <1    | 0.02  |
| 1694080 | Rock Pulp                        | 0.09 | 7.232  | 8.2   | 184.6 | 16.6  | 66    | 0.8   | 11.8  | 10.3  | 520   | 4.12  | 12.1  | 6915.4 | 2.3   | 58    | 0.2   | 3.9   | 0.5   | 96    | 0.82  |
| 1694081 | Rab Sample                       | 2.32 | 0.032  | 0.9   | 4.6   | 46.9  | 52    | 0.5   | 1.1   | 1.6   | 154   | 0.67  | 122.1 | 27.5   | 11.6  | 6     | 1.8   | 0.9   | 0.1   | <1    | 0.03  |
| 1694082 | Rab Sample                       | 3.36 | 0.029  | 0.9   | 4.1   | 47.7  | 49    | 0.5   | 1.1   | 1.3   | 153   | 0.68  | 110.4 | 28.1   | 13.0  | 6     | 1.7   | 0.9   | 0.1   | <1    | 0.03  |
| 1694083 | Rab Sample                       | 2.85 | 0.043  | 0.8   | 3.9   | 37.0  | 47    | 0.4   | 0.9   | 0.6   | 51    | 0.65  | 107.6 | 43.6   | 12.8  | 6     | 1.3   | 1.1   | 0.1   | <1    | 0.02  |
| 1694084 | Rab Sample                       | 3.22 | 0.208  | 0.9   | 3.1   | 28.5  | 47    | 0.3   | 0.8   | 1.0   | 76    | 0.72  | 110.3 | 27.5   | 13.3  | 5     | 1.3   | 0.9   | 0.2   | <1    | 0.02  |
| 1694085 | Rab Sample                       | 3.19 | 0.009  | 0.9   | 2.8   | 27.0  | 58    | 0.3   | 1.1   | 0.9   | 91    | 0.78  | 77.8  | 8.1    | 13.3  | 5     | 1.0   | 0.6   | 0.1   | <1    | 0.02  |
| 1694086 | Rab Sample                       | 3.47 | 0.010  | 1.0   | 3.0   | 42.0  | 63    | 0.4   | 1.3   | 0.8   | 99    | 0.90  | 67.4  | 10.9   | 13.7  | 6     | 0.8   | 0.7   | <0.1  | <1    | 0.02  |
| 1694087 | Rab Sample                       | 3.52 | 0.009  | 0.9   | 3.7   | 25.2  | 49    | 0.3   | 0.9   | 0.6   | 76    | 0.81  | 68.8  | 8.4    | 14.6  | 5     | 0.9   | 0.8   | <0.1  | <1    | 0.02  |
| 1694088 | Rab Sample                       | 3.41 | 0.007  | 0.8   | 4.3   | 58.1  | 67    | 0.4   | 0.9   | 0.6   | 53    | 1.06  | 50.4  | 7.1    | 11.9  | 5     | 0.5   | 0.4   | 0.2   | <1    | 0.02  |
| 1694089 | Rab Sample                       | 3.41 | 0.009  | 0.9   | 3.8   | 46.9  | 51    | 0.4   | 1.1   | 0.3   | 33    | 0.89  | 58.3  | 10.8   | 12.5  | 6     | 0.5   | 0.6   | <0.1  | <1    | 0.01  |
| 1694090 | Rab Sample                       | 3.27 | 0.009  | 0.9   | 3.4   | 56.3  | 40    | 0.4   | 1.1   | 1.3   | 144   | 0.61  | 47.8  | 102.5  | 12.6  | 7     | 0.8   | 1.1   | 0.1   | <1    | 0.02  |
| 1694091 | Rab Sample                       | 3.38 | 0.009  | 0.9   | 3.7   | 59.6  | 22    | 0.3   | 0.5   | 0.3   | 29    | 0.51  | 37.4  | 5.0    | 13.0  | 4     | 0.3   | 0.7   | <0.1  | <1    | <0.01 |
| 1694092 | Rab Sample                       | 3.63 | 0.009  | 1.1   | 3.0   | 51.1  | 18    | 0.3   | 0.8   | 0.3   | 29    | 0.55  | 45.0  | 8.2    | 11.7  | 4     | 0.4   | 1.0   | <0.1  | <1    | <0.01 |
| 1694093 | Rab Sample                       | 3.75 | 0.018  | 1.1   | 3.5   | 57.9  | 35    | 0.5   | 0.8   | 0.2   | 20    | 0.78  | 266.2 | 18.7   | 12.3  | 5     | 1.6   | 2.3   | <0.1  | <1    | 0.01  |
| 1694094 | Rab Sample                       | 3.28 | 0.018  | 1.0   | 4.9   | 102.3 | 40    | 0.6   | 0.8   | 0.2   | 27    | 0.81  | 337.4 | 15.5   | 12.1  | 5     | 1.7   | 1.8   | <0.1  | <1    | 0.02  |
| 1694095 | Rab Sample                       | 3.31 | 0.005  | 0.9   | 3.4   | 71.5  | 32    | 0.3   | 0.8   | 0.6   | 349   | 0.63  | 141.2 | 3.0    | 11.2  | 5     | 0.5   | 0.7   | <0.1  | <1    | 0.02  |
| 1694096 | Rab Sample                       | 3.33 | 0.007  | 0.8   | 2.3   | 35.1  | 23    | 0.2   | 0.6   | 0.7   | 113   | 0.49  | 104.5 | 3.4    | 10.6  | 4     | 0.3   | 0.6   | <0.1  | <1    | 0.02  |
| 1694097 | Rab Sample                       | 3.10 | 0.007  | 1.1   | 3.5   | 25.3  | 18    | 0.3   | 0.7   | 0.2   | 21    | 0.55  | 95.6  | 3.5    | 11.6  | 4     | 0.2   | 0.5   | 0.4   | <1    | 0.01  |



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method<br>Analyte<br>Unit<br>MDL | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|         |                                  | P     | La    | Cr    | Mg    | Ba    | Ti     | B     | Al    | Na    | K     | W     | Hg    | Sc    | Tl    | S     | Ga    | Se    | Te    |
|         |                                  | %     | ppm   | ppm   | %     | ppm   | %      | ppm   | %     | %     | %     | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppm   | ppm   |
|         |                                  | 0.001 | 1     | 1     | 0.01  | 1     | 0.001  | 20    | 0.01  | 0.001 | 0.01  | 0.1   | 0.01  | 0.1   | 0.1   | 0.1   | 0.05  | 1     | 0.5   |
| 1694068 | Rab Sample                       | 0.007 | 40    | 7     | 0.07  | 294   | 0.008  | <20   | 0.38  | 0.014 | 0.18  | 0.6   | 0.01  | 2.1   | <0.1  | <0.05 | 2     | <0.5  | <0.2  |
| 1694069 | Rab Sample                       | 0.006 | 43    | 4     | 0.02  | 149   | 0.001  | <20   | 0.23  | 0.020 | 0.22  | 1.2   | 0.02  | 1.6   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694070 | Rab Sample                       | 0.005 | 41    | 1     | 0.02  | 165   | 0.001  | <20   | 0.21  | 0.016 | 0.20  | 0.8   | 0.03  | 1.0   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694071 | Rab Sample                       | 0.005 | 46    | 2     | 0.01  | 184   | 0.001  | <20   | 0.20  | 0.019 | 0.21  | 0.8   | 0.01  | 1.0   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694072 | Rab Sample                       | 0.004 | 42    | 2     | 0.02  | 195   | <0.001 | <20   | 0.27  | 0.018 | 0.23  | 0.7   | 0.02  | 1.5   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694073 | Rab Sample                       | 0.004 | 33    | 3     | 0.03  | 174   | 0.001  | <20   | 0.28  | 0.022 | 0.22  | 1.0   | 0.03  | 2.4   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694074 | Rab Sample                       | 0.005 | 37    | 3     | 0.02  | 170   | 0.001  | <20   | 0.23  | 0.022 | 0.21  | 1.2   | 0.03  | 1.7   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694075 | Rab Sample                       | 0.004 | 37    | 4     | 0.02  | 202   | 0.001  | <20   | 0.24  | 0.020 | 0.24  | 0.9   | 0.04  | 1.1   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694076 | Rab Sample                       | 0.005 | 30    | 2     | 0.01  | 162   | <0.001 | <20   | 0.22  | 0.019 | 0.24  | 0.8   | 0.04  | 0.8   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694077 | Rab Sample                       | 0.006 | 42    | 3     | 0.01  | 170   | <0.001 | <20   | 0.20  | 0.018 | 0.24  | 0.7   | 0.05  | 1.1   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694078 | Rab Sample                       | 0.004 | 34    | 3     | 0.01  | 368   | <0.001 | <20   | 0.22  | 0.006 | 0.26  | 0.7   | 0.05  | 1.0   | 0.1   | <0.05 | <1    | <0.5  | <0.2  |
| 1694079 | Rab Sample                       | 0.003 | 33    | 4     | 0.02  | 778   | <0.001 | <20   | 0.26  | 0.009 | 0.25  | 0.7   | 0.06  | 1.0   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694080 | Rock Pulp                        | 0.055 | 6     | 16    | 0.76  | 104   | 0.104  | <20   | 1.44  | 0.161 | 0.21  | 3.0   | 0.19  | 2.8   | <0.1  | <0.05 | 5     | <0.5  | <0.2  |
| 1694081 | Rab Sample                       | 0.005 | 39    | 3     | 0.02  | 219   | 0.001  | <20   | 0.29  | 0.010 | 0.22  | 0.7   | 0.05  | 1.4   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694082 | Rab Sample                       | 0.005 | 39    | 3     | 0.02  | 217   | 0.001  | <20   | 0.30  | 0.010 | 0.22  | 0.6   | 0.05  | 1.2   | 0.1   | <0.05 | 1     | <0.5  | <0.2  |
| 1694083 | Rab Sample                       | 0.007 | 40    | 3     | 0.02  | 186   | 0.001  | <20   | 0.27  | 0.008 | 0.21  | 0.6   | 0.05  | 1.6   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694084 | Rab Sample                       | 0.006 | 47    | 4     | 0.02  | 193   | 0.001  | <20   | 0.30  | 0.015 | 0.24  | 0.5   | 0.02  | 1.7   | <0.1  | <0.05 | 2     | <0.5  | <0.2  |
| 1694085 | Rab Sample                       | 0.007 | 46    | 4     | 0.03  | 210   | 0.002  | <20   | 0.30  | 0.016 | 0.23  | 0.6   | 0.02  | 2.6   | <0.1  | <0.05 | 2     | <0.5  | <0.2  |
| 1694086 | Rab Sample                       | 0.006 | 40    | 5     | 0.03  | 205   | 0.002  | <20   | 0.33  | 0.022 | 0.22  | 0.8   | 0.03  | 2.7   | <0.1  | <0.05 | 2     | <0.5  | <0.2  |
| 1694087 | Rab Sample                       | 0.005 | 42    | 4     | 0.03  | 171   | 0.002  | <20   | 0.33  | 0.021 | 0.23  | 0.7   | 0.03  | 2.5   | <0.1  | <0.05 | 2     | <0.5  | <0.2  |
| 1694088 | Rab Sample                       | 0.005 | 39    | 4     | 0.03  | 200   | 0.001  | <20   | 0.32  | 0.016 | 0.21  | 0.6   | 0.03  | 2.7   | 0.1   | <0.05 | 2     | <0.5  | <0.2  |
| 1694089 | Rab Sample                       | 0.004 | 40    | 4     | 0.02  | 170   | <0.001 | <20   | 0.25  | 0.010 | 0.21  | 0.8   | 0.07  | 2.1   | 0.1   | <0.05 | 1     | <0.5  | <0.2  |
| 1694090 | Rab Sample                       | 0.006 | 44    | 4     | 0.02  | 180   | <0.001 | <20   | 0.26  | 0.014 | 0.23  | 0.5   | 0.05  | 1.5   | 0.2   | <0.05 | 1     | <0.5  | <0.2  |
| 1694091 | Rab Sample                       | 0.005 | 42    | 4     | 0.01  | 128   | 0.001  | <20   | 0.22  | 0.017 | 0.20  | 0.7   | 0.05  | 2.2   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694092 | Rab Sample                       | 0.005 | 33    | 4     | <0.01 | 120   | 0.001  | <20   | 0.23  | 0.021 | 0.20  | 0.7   | 0.02  | 1.6   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694093 | Rab Sample                       | 0.005 | 40    | 4     | 0.01  | 143   | <0.001 | <20   | 0.22  | 0.013 | 0.19  | 0.7   | 0.04  | 1.2   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694094 | Rab Sample                       | 0.004 | 42    | 4     | 0.01  | 170   | <0.001 | <20   | 0.22  | 0.005 | 0.22  | 0.5   | 0.05  | 1.0   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694095 | Rab Sample                       | 0.005 | 32    | 4     | <0.01 | 217   | <0.001 | <20   | 0.22  | 0.010 | 0.22  | 0.6   | 0.03  | 0.8   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694096 | Rab Sample                       | 0.005 | 31    | 3     | <0.01 | 182   | <0.001 | <20   | 0.24  | 0.015 | 0.25  | 0.5   | 0.02  | 0.8   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694097 | Rab Sample                       | 0.004 | 30    | 4     | <0.01 | 121   | <0.001 | <20   | 0.19  | 0.017 | 0.18  | 0.8   | 0.04  | 0.7   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 3 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method<br>Analyte<br>Unit<br>MDL | WGHT | FA430  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|
|         |                                  | Wgt  | Au     | Mo    | Cu    | Pb    | Zn    | Ag    | Ni    | Co    | Mn    | Fe    | As    | Au     | Th    | Sr    | Cd    | Sb    | Bi    | V     | Ca    |
|         |                                  | kg   | ppm    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppb    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     |
|         |                                  | 0.01 | 0.005  | 0.1   | 0.1   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     | 0.01  | 0.5   | 0.5    | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     | 0.01  |
| 1694098 | Rab Sample                       | 2.90 | 0.008  | 0.8   | 2.4   | 14.8  | 13    | 0.2   | 0.6   | 0.1   | 18    | 0.61  | 93.6  | 4.9    | 11.9  | 4     | 0.2   | 0.5   | 0.1   | <1    | 0.02  |
| 1694099 | Rab Sample                       | 3.05 | 0.011  | 0.9   | 2.1   | 13.1  | 10    | 0.2   | 0.7   | 0.1   | 20    | 0.52  | 82.4  | 6.4    | 12.3  | 5     | 0.1   | 0.4   | <0.1  | <1    | 0.02  |
| 1694100 | Rock Pulp                        | 0.08 | 7.069  | 8.5   | 168.8 | 17.7  | 68    | 0.9   | 12.8  | 11.4  | 548   | 4.15  | 12.5  | 8711.8 | 2.6   | 61    | 0.2   | 4.2   | 0.5   | 97    | 0.82  |
| 1694101 | Rab Sample                       | 3.23 | 0.017  | 1.0   | 3.6   | 24.4  | 12    | 0.5   | 0.8   | 0.2   | 21    | 0.52  | 78.2  | 11.0   | 11.3  | 4     | 0.2   | 0.6   | <0.1  | <1    | 0.01  |
| 1694102 | Rab Sample                       | 3.35 | 0.022  | 1.2   | 3.5   | 39.1  | 16    | 0.4   | 0.8   | 0.2   | 31    | 0.91  | 147.6 | 21.6   | 13.3  | 5     | 0.2   | 0.7   | <0.1  | <1    | 0.02  |
| 1694103 | Rab Sample                       | 3.25 | 0.051  | 0.9   | 3.2   | 20.8  | 12    | 0.7   | 0.7   | 0.2   | 21    | 0.81  | 124.8 | 53.5   | 13.0  | 7     | 0.2   | 0.6   | 0.2   | <1    | 0.02  |
| 1694104 | Rab Sample                       | 3.32 | 0.074  | 1.2   | 3.6   | 21.9  | 22    | 0.4   | 0.8   | 0.2   | 31    | 0.80  | 154.7 | 66.0   | 14.8  | 18    | 0.3   | 0.6   | 0.3   | <1    | 0.03  |
| 1694105 | Rab Sample                       | 3.40 | 0.006  | 1.1   | 3.8   | 16.9  | 63    | 0.2   | 1.1   | 0.8   | 89    | 0.83  | 22.0  | 5.1    | 14.7  | 86    | 1.1   | 0.8   | 0.1   | <1    | 0.74  |
| 1694106 | Rab Sample                       | 3.76 | <0.005 | 1.3   | 5.4   | 14.6  | 11    | 0.2   | 0.9   | 0.6   | 114   | 0.81  | 31.8  | 3.3    | 13.8  | 125   | 0.3   | 1.0   | 0.1   | <1    | 1.26  |
| 1694107 | Rab Sample                       | 3.87 | <0.005 | 1.7   | 3.4   | 28.2  | 9     | 0.3   | 0.8   | 0.7   | 108   | 0.86  | 14.7  | 2.2    | 13.3  | 82    | 0.3   | 1.0   | 0.1   | <1    | 0.90  |
| 1694108 | Rab Sample                       | 3.56 | <0.005 | 1.2   | 5.4   | 29.1  | 13    | 0.4   | 1.0   | 0.7   | 67    | 0.66  | 20.3  | 2.4    | 14.0  | 37    | 0.7   | 0.5   | 0.1   | <1    | 0.43  |
| 1694109 | Rab Sample                       | 3.94 | <0.005 | 1.1   | 2.4   | 22.9  | 7     | 0.2   | 0.7   | 0.5   | 63    | 0.56  | 7.5   | 2.8    | 14.0  | 77    | 0.5   | 0.5   | 0.1   | <1    | 0.86  |
| 1694110 | Rab Sample                       | 3.83 | <0.005 | 1.3   | 2.9   | 14.6  | 6     | 0.2   | 0.7   | 0.4   | 66    | 0.66  | 8.0   | 3.8    | 13.0  | 88    | 0.3   | 0.4   | 0.1   | <1    | 0.88  |
| 1694111 | Rab Sample                       | 3.90 | <0.005 | 1.3   | 4.7   | 27.8  | 11    | 0.6   | 0.8   | 0.6   | 101   | 0.59  | 4.5   | 2.4    | 13.1  | 237   | 0.6   | 0.5   | 0.1   | <1    | 2.01  |
| 1694112 | Rab Sample                       | 4.06 | <0.005 | 1.3   | 5.4   | 17.0  | 12    | 0.3   | 1.3   | 0.8   | 107   | 0.93  | 5.2   | <0.5   | 13.6  | 113   | 0.4   | 0.3   | 0.1   | <1    | 0.99  |
| 1694113 | Rab Sample                       | 3.96 | <0.005 | 1.4   | 2.9   | 21.4  | 11    | 0.3   | 0.7   | 0.4   | 77    | 0.62  | 8.0   | <0.5   | 14.0  | 59    | 0.3   | 0.6   | 0.1   | <1    | 0.59  |
| 1694114 | Rab Sample                       | 3.64 | <0.005 | 1.3   | 3.7   | 22.7  | 16    | 0.3   | 0.9   | 0.7   | 120   | 0.79  | 24.7  | 1.0    | 14.1  | 127   | 0.5   | 0.7   | 0.1   | <1    | 1.26  |
| 1694115 | Rab Sample                       | 3.74 | 0.857  | 1.4   | 5.3   | 17.6  | 19    | 1.4   | 1.0   | 0.7   | 60    | 0.69  | 20.5  | 792.1  | 13.4  | 35    | 0.4   | 0.5   | 0.1   | <1    | 0.27  |
| 1694116 | Rab Sample                       | 4.03 | 0.005  | 1.6   | 4.4   | 19.9  | 21    | 0.4   | 1.0   | 0.6   | 87    | 0.72  | 9.1   | 1.9    | 12.7  | 96    | 0.3   | 0.9   | 0.1   | <1    | 1.11  |
| 1694117 | Rab Sample                       | 4.19 | <0.005 | 1.4   | 2.9   | 24.6  | 27    | 0.3   | 0.9   | 0.3   | 140   | 0.62  | 3.8   | 0.7    | 10.5  | 142   | 0.3   | 0.6   | 0.1   | <1    | 1.55  |
| 1694118 | Rab Sample                       | 4.15 | <0.005 | 1.5   | 4.9   | 18.8  | 37    | 0.5   | 1.1   | 0.7   | 123   | 0.73  | 4.0   | <0.5   | 11.1  | 126   | 0.3   | 0.9   | <0.1  | <1    | 1.08  |
| 1694119 | Rab Sample                       | 3.90 | <0.005 | 1.5   | 4.1   | 24.8  | 34    | 0.3   | 0.9   | 0.7   | 125   | 0.70  | 2.4   | 1.7    | 13.6  | 147   | 0.4   | 0.8   | 0.2   | <1    | 1.35  |
| 1694120 | Rock                             | 0.61 | <0.005 | <0.1  | 0.4   | 0.5   | <1    | <0.1  | 0.6   | 0.5   | 89    | 0.06  | <0.5  | <0.5   | <0.1  | 71    | <0.1  | <0.1  | <0.1  | <1    | 32.35 |
| 1694121 | Rab Sample                       | 3.73 | <0.005 | 1.7   | 5.0   | 17.5  | 29    | 0.3   | 1.1   | 0.9   | 115   | 0.67  | 4.5   | 1.0    | 8.6   | 122   | 0.3   | 0.9   | <0.1  | <1    | 1.04  |
| 1694122 | Rab Sample                       | 4.01 | <0.005 | 1.7   | 4.4   | 19.0  | 21    | 0.3   | 1.1   | 0.8   | 145   | 0.74  | 8.3   | <0.5   | 10.9  | 131   | 0.4   | 0.7   | <0.1  | <1    | 1.23  |
| 1694123 | Rab Sample                       | 4.28 | <0.005 | 2.4   | 4.3   | 17.4  | 21    | 0.2   | 0.8   | 0.7   | 101   | 0.56  | 5.5   | <0.5   | 8.0   | 99    | 0.5   | 0.4   | 0.1   | <1    | 0.89  |
| 1694124 | Rab Sample                       | 4.06 | <0.005 | 1.7   | 3.5   | 13.3  | 27    | 0.2   | 0.9   | 0.6   | 77    | 0.49  | 1.6   | <0.5   | 5.2   | 65    | 0.1   | 0.3   | <0.1  | <1    | 0.57  |
| 1694125 | Rab Sample                       | 4.18 | <0.005 | 1.9   | 4.5   | 14.0  | 22    | 0.3   | 1.2   | 0.8   | 86    | 0.54  | 2.1   | <0.5   | 5.1   | 66    | 0.2   | 0.4   | 0.1   | <1    | 0.58  |
| 1694126 | Rab Sample                       | 3.97 | <0.005 | 1.8   | 4.5   | 16.9  | 23    | 0.3   | 1.3   | 0.9   | 99    | 0.59  | 2.3   | 1.1    | 5.0   | 74    | 0.3   | 0.4   | 0.1   | <1    | 0.59  |
| 1694127 | Rab Sample                       | 4.28 | <0.005 | 2.2   | 4.2   | 14.4  | 19    | 0.3   | 1.0   | 0.7   | 92    | 0.51  | 1.7   | 0.5    | 4.9   | 84    | 0.2   | 0.6   | 0.1   | <1    | 0.62  |



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 3 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method     | Analyte | AQ200 |       |       |      |        |     |       |       |       |       |       |     |      |       |     |      |      | AQ200 |     |
|---------|------------|---------|-------|-------|-------|------|--------|-----|-------|-------|-------|-------|-------|-----|------|-------|-----|------|------|-------|-----|
|         |            |         | P     | La    | Cr    | Mg   | Ba     | Ti  | B     | Al    | Na    | K     | W     | Hg  | Sc   | Tl    | S   | Ga   | Se   |       | Te  |
|         |            |         | %     | ppm   | ppm   | %    | ppm    | %   | ppm   | %     | %     | %     | ppm   | ppm | ppm  | ppm   | %   | ppm  | ppm  |       | ppm |
|         |            |         | MDL   | 0.001 | 1     | 1    | 0.01   | 1   | 0.001 | 20    | 0.01  | 0.001 | 0.01  | 0.1 | 0.01 | 0.1   | 0.1 | 0.05 | 1    |       | 0.5 |
| 1694098 | Rab Sample | 0.005   | 31    | 3     | <0.01 | 114  | <0.001 | <20 | 0.22  | 0.016 | 0.18  | 0.4   | 0.03  | 0.7 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694099 | Rab Sample | 0.004   | 28    | 3     | <0.01 | 139  | <0.001 | <20 | 0.23  | 0.015 | 0.18  | 0.6   | 0.02  | 0.8 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694100 | Rock Pulp  | 0.061   | 7     | 16    | 0.77  | 113  | 0.112  | <20 | 1.45  | 0.157 | 0.20  | 3.7   | 0.23  | 2.6 | <0.1 | <0.05 | 5   | <0.5 | <0.2 |       |     |
| 1694101 | Rab Sample | 0.004   | 29    | 4     | <0.01 | 138  | <0.001 | <20 | 0.22  | 0.017 | 0.21  | 0.6   | 0.05  | 1.0 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694102 | Rab Sample | 0.006   | 37    | 6     | 0.02  | 162  | <0.001 | <20 | 0.32  | 0.017 | 0.22  | 0.6   | 0.05  | 1.2 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694103 | Rab Sample | 0.005   | 40    | 5     | 0.02  | 162  | <0.001 | <20 | 0.26  | 0.012 | 0.22  | 0.7   | 0.03  | 1.1 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694104 | Rab Sample | 0.006   | 38    | 5     | 0.03  | 1258 | <0.001 | <20 | 0.34  | 0.014 | 0.25  | 0.8   | 0.03  | 1.4 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694105 | Rab Sample | 0.006   | 62    | 4     | 0.04  | 1709 | 0.001  | <20 | 0.36  | 0.023 | 0.18  | 1.0   | 0.01  | 2.4 | <0.1 | 0.05  | 1   | <0.5 | <0.2 |       |     |
| 1694106 | Rab Sample | 0.006   | 45    | 5     | 0.03  | 1022 | 0.002  | <20 | 0.36  | 0.033 | 0.20  | 1.5   | 0.03  | 2.9 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694107 | Rab Sample | 0.005   | 42    | 6     | 0.03  | 687  | 0.002  | <20 | 0.35  | 0.024 | 0.20  | 1.5   | 0.01  | 2.6 | 0.1  | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694108 | Rab Sample | 0.004   | 46    | 6     | 0.03  | 875  | <0.001 | <20 | 0.33  | 0.007 | 0.27  | 1.3   | 0.01  | 2.1 | 0.1  | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694109 | Rab Sample | 0.006   | 44    | 5     | 0.04  | 594  | 0.001  | <20 | 0.33  | 0.010 | 0.27  | 1.0   | 0.01  | 2.4 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694110 | Rab Sample | 0.005   | 40    | 5     | 0.04  | 745  | 0.001  | <20 | 0.38  | 0.015 | 0.27  | 1.1   | 0.02  | 2.5 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694111 | Rab Sample | 0.005   | 40    | 5     | 0.04  | 1064 | <0.001 | <20 | 0.31  | 0.015 | 0.24  | 1.4   | 0.05  | 4.0 | 0.1  | 0.08  | <1  | <0.5 | <0.2 |       |     |
| 1694112 | Rab Sample | 0.005   | 41    | 8     | 0.03  | 770  | <0.001 | <20 | 0.37  | 0.028 | 0.24  | 1.9   | 0.05  | 2.9 | 0.1  | 0.10  | 1   | <0.5 | <0.2 |       |     |
| 1694113 | Rab Sample | 0.006   | 41    | 5     | 0.03  | 329  | 0.001  | <20 | 0.33  | 0.023 | 0.22  | 1.3   | 0.04  | 3.0 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694114 | Rab Sample | 0.006   | 45    | 6     | 0.02  | 520  | <0.001 | <20 | 0.32  | 0.027 | 0.22  | 1.6   | 0.04  | 3.2 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694115 | Rab Sample | 0.006   | 43    | 7     | 0.03  | 652  | 0.001  | <20 | 0.30  | 0.009 | 0.28  | 1.6   | 0.04  | 2.8 | 0.1  | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694116 | Rab Sample | 0.006   | 41    | 6     | 0.03  | 743  | 0.002  | <20 | 0.35  | 0.021 | 0.24  | 1.6   | 0.01  | 2.7 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694117 | Rab Sample | 0.006   | 38    | 6     | 0.02  | 709  | 0.002  | <20 | 0.37  | 0.015 | 0.23  | 3.3   | <0.01 | 2.0 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694118 | Rab Sample | 0.006   | 36    | 7     | 0.01  | 584  | 0.002  | <20 | 0.35  | 0.024 | 0.21  | 3.5   | 0.01  | 2.1 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694119 | Rab Sample | 0.007   | 41    | 5     | 0.01  | 1756 | 0.002  | <20 | 0.29  | 0.025 | 0.19  | 2.4   | <0.01 | 2.2 | <0.1 | 0.06  | <1  | <0.5 | <0.2 |       |     |
| 1694120 | Rock       | 0.005   | 1     | <1    | 0.45  | 14   | 0.001  | <20 | 0.02  | 0.003 | <0.01 | <0.1  | <0.01 | 0.2 | <0.1 | <0.05 | <1  | <0.5 | <0.2 |       |     |
| 1694121 | Rab Sample | 0.007   | 26    | 7     | 0.01  | 1758 | 0.005  | <20 | 0.36  | 0.036 | 0.18  | 5.2   | <0.01 | 1.7 | 0.1  | 0.11  | 1   | <0.5 | <0.2 |       |     |
| 1694122 | Rab Sample | 0.006   | 36    | 7     | 0.01  | 677  | 0.003  | <20 | 0.37  | 0.031 | 0.22  | 5.0   | <0.01 | 2.3 | <0.1 | 0.09  | 1   | <0.5 | <0.2 |       |     |
| 1694123 | Rab Sample | 0.006   | 26    | 6     | 0.01  | 640  | 0.005  | <20 | 0.36  | 0.029 | 0.21  | 5.0   | <0.01 | 1.7 | <0.1 | 0.08  | 1   | <0.5 | <0.2 |       |     |
| 1694124 | Rab Sample | 0.006   | 16    | 6     | 0.01  | 987  | 0.008  | <20 | 0.37  | 0.035 | 0.19  | 4.2   | <0.01 | 1.3 | <0.1 | <0.05 | 1   | <0.5 | <0.2 |       |     |
| 1694125 | Rab Sample | 0.006   | 15    | 7     | 0.02  | 1295 | 0.014  | <20 | 0.44  | 0.031 | 0.22  | 4.7   | <0.01 | 1.4 | 0.1  | 0.05  | 2   | <0.5 | <0.2 |       |     |
| 1694126 | Rab Sample | 0.006   | 15    | 8     | 0.01  | 1299 | 0.011  | <20 | 0.40  | 0.028 | 0.19  | 5.7   | <0.01 | 1.3 | <0.1 | <0.05 | 2   | <0.5 | <0.2 |       |     |
| 1694127 | Rab Sample | 0.006   | 15    | 7     | 0.01  | 2309 | 0.013  | <20 | 0.41  | 0.034 | 0.18  | 6.6   | <0.01 | 1.3 | <0.1 | 0.07  | 2   | <0.5 | <0.2 |       |     |



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 4 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method     | WGHT | FA430  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|------------|------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|         | Analyte    | Wgt  | Au     | Mo    | Cu    | Pb    | Zn    | Ag    | Ni    | Co    | Mn    | Fe    | As    | Au    | Th    | Sr    | Cd    | Sb    | Bi    | V     |
|         | Unit       | kg   | ppm    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppb   | ppm   | ppm   | ppm   | ppm   | ppm   | %     |
|         | MDL        | 0.01 | 0.005  | 0.1   | 0.1   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     | 0.01  | 0.5   | 0.5   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     |
| 1694128 | Rab Sample | 3.90 | 0.006  | 2.0   | 4.8   | 17.7  | 20    | 0.3   | 1.0   | 0.9   | 63    | 0.44  | 2.4   | <0.5  | 2.9   | 52    | 0.3   | 0.5   | 0.1   | <1    |
| 1694129 | Rab Sample | 4.09 | <0.005 | 2.5   | 3.6   | 15.6  | 31    | 0.3   | 1.2   | 0.9   | 126   | 0.51  | 1.5   | <0.5  | 3.5   | 77    | 0.2   | 0.5   | 0.1   | <1    |
| 1694130 | Rab Sample | 4.23 | <0.005 | 2.2   | 6.3   | 15.4  | 27    | 0.4   | 1.2   | 1.1   | 78    | 0.53  | 1.9   | <0.5  | 4.7   | 75    | 0.3   | 0.7   | 0.1   | <1    |
| 1694131 | Rab Sample | 3.81 | <0.005 | 1.8   | 4.8   | 17.8  | 20    | 0.3   | 1.1   | 0.9   | 121   | 0.64  | 2.0   | 0.5   | 7.5   | 98    | 0.3   | 0.6   | 0.1   | <1    |
| 1694132 | Rab Sample | 3.77 | <0.005 | 1.5   | 4.7   | 21.3  | 18    | 0.3   | 0.9   | 0.7   | 157   | 0.84  | 3.4   | 0.9   | 13.4  | 169   | 0.4   | 0.9   | 0.3   | <1    |
| 1694133 | Rab Sample | 3.83 | <0.005 | 1.5   | 4.5   | 19.3  | 10    | 0.3   | 1.2   | 0.7   | 86    | 0.67  | 4.4   | <0.5  | 13.8  | 96    | 0.4   | 0.6   | 0.2   | <1    |
| 1694134 | Rab Sample | 4.11 | <0.005 | 1.8   | 4.4   | 20.1  | 11    | 0.3   | 1.2   | 0.7   | 76    | 0.59  | 2.9   | <0.5  | 13.2  | 80    | 0.4   | 0.4   | 0.2   | <1    |
| 1694135 | Rab Sample | 3.58 | 0.007  | 1.4   | 4.6   | 28.9  | 26    | 0.5   | 1.1   | 0.7   | 55    | 0.53  | 25.7  | 2.3   | 13.8  | 34    | 0.4   | 0.3   | 0.2   | <1    |
| 1694136 | Rab Sample | 3.78 | 0.022  | 1.7   | 3.2   | 16.5  | 24    | 0.3   | 1.3   | 0.6   | 90    | 0.55  | 93.9  | 12.8  | 14.8  | 29    | 0.4   | 0.3   | 0.2   | <1    |



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 4 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000213.1

|         | Method<br>Analyte<br>Unit<br>MDL | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|         |                                  | P     | La    | Cr    | Mg    | Ba    | Ti     | B     | Al    | Na    | K     | W     | Hg    | Sc    | Tl    | S     | Ga    | Se    | Te    |
|         |                                  | %     | ppm   | ppm   | %     | ppm   | %      | ppm   | %     | %     | %     | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppm   | ppm   |
|         |                                  | 0.001 | 1     | 1     | 0.01  | 1     | 0.001  | 20    | 0.01  | 0.001 | 0.01  | 0.1   | 0.01  | 0.1   | 0.1   | 0.05  | 1     | 0.5   | 0.2   |
| 1694128 | Rab Sample                       | 0.006 | 9     | 6     | <0.01 | 1220  | 0.016  | <20   | 0.37  | 0.026 | 0.17  | 6.3   | <0.01 | 1.0   | <0.1  | 0.08  | 1     | <0.5  | <0.2  |
| 1694129 | Rab Sample                       | 0.006 | 11    | 8     | 0.01  | 2096  | 0.014  | <20   | 0.38  | 0.033 | 0.19  | 6.9   | <0.01 | 1.1   | <0.1  | 0.10  | 2     | <0.5  | <0.2  |
| 1694130 | Rab Sample                       | 0.007 | 14    | 8     | 0.01  | 1930  | 0.010  | <20   | 0.38  | 0.039 | 0.17  | 8.0   | <0.01 | 1.2   | <0.1  | 0.12  | 2     | <0.5  | <0.2  |
| 1694131 | Rab Sample                       | 0.006 | 22    | 7     | 0.01  | 1347  | 0.006  | <20   | 0.37  | 0.034 | 0.19  | 6.3   | <0.01 | 1.9   | <0.1  | 0.10  | 1     | <0.5  | <0.2  |
| 1694132 | Rab Sample                       | 0.006 | 42    | 7     | 0.02  | 1228  | 0.002  | <20   | 0.39  | 0.032 | 0.22  | 3.8   | <0.01 | 3.4   | 0.2   | 0.06  | 2     | <0.5  | <0.2  |
| 1694133 | Rab Sample                       | 0.006 | 45    | 6     | 0.03  | 784   | 0.002  | <20   | 0.35  | 0.017 | 0.28  | 3.3   | <0.01 | 2.8   | 0.1   | 0.07  | 1     | <0.5  | <0.2  |
| 1694134 | Rab Sample                       | 0.006 | 44    | 7     | 0.04  | 467   | 0.002  | <20   | 0.33  | 0.017 | 0.29  | 2.9   | <0.01 | 2.6   | 0.1   | <0.05 | <1    | <0.5  | <0.2  |
| 1694135 | Rab Sample                       | 0.005 | 42    | 6     | 0.05  | 417   | <0.001 | <20   | 0.31  | 0.009 | 0.29  | 3.4   | 0.01  | 1.8   | 0.1   | 0.08  | <1    | <0.5  | <0.2  |
| 1694136 | Rab Sample                       | 0.006 | 50    | 7     | 0.06  | 238   | <0.001 | <20   | 0.35  | 0.009 | 0.32  | 1.7   | 0.02  | 1.7   | 0.1   | <0.05 | <1    | <0.5  | <0.2  |



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 1 of 2

**Part:** 1 of 2

## QUALITY CONTROL REPORT

WHI18000213.1

|                        | Method<br>Analyte<br>Unit<br>MDL | WGHT | FA430  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|------------------------|----------------------------------|------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|                        |                                  | Wgt  | Au     | Mo    | Cu    | Pb    | Zn    | Ag    | Ni    | Co    | Mn    | Fe    | As    | Au    | Th    | Sr    | Cd    | Sb    | Bi    | V     | Ca    |
|                        |                                  | kg   | ppm    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppb   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     |
|                        |                                  | 0.01 | 0.005  | 0.1   | 0.1   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 0.1   | 1     | 0.01  | 0.5   | 0.5   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     |
| Pulp Duplicates        |                                  |      |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694076                | Rab Sample                       | 3.42 | 0.008  | 0.8   | 2.6   | 24.3  | 27    | 0.2   | 0.9   | 0.3   | 46    | 0.54  | 78.0  | 4.7   | 11.7  | 3     | 0.6   | 0.7   | 0.1   | <1    | 0.01  |
| REP 1694076            | QC                               |      |        | 0.9   | 2.6   | 26.6  | 28    | 0.2   | 0.7   | 0.4   | 46    | 0.52  | 84.9  | 4.5   | 13.1  | 4     | 0.5   | 0.7   | 0.1   | <1    | 0.01  |
| 1694110                | Rab Sample                       | 3.83 | <0.005 | 1.3   | 2.9   | 14.6  | 6     | 0.2   | 0.7   | 0.4   | 66    | 0.66  | 8.0   | 3.8   | 13.0  | 88    | 0.3   | 0.4   | 0.1   | <1    | 0.88  |
| REP 1694110            | QC                               |      | <0.005 |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694111                | Rab Sample                       | 3.90 | <0.005 | 1.3   | 4.7   | 27.8  | 11    | 0.6   | 0.8   | 0.6   | 101   | 0.59  | 4.5   | 2.4   | 13.1  | 237   | 0.6   | 0.5   | 0.1   | <1    | 2.01  |
| REP 1694111            | QC                               |      |        | 1.4   | 4.8   | 28.1  | 12    | 0.6   | 0.9   | 0.6   | 107   | 0.63  | 4.8   | <0.5  | 13.6  | 249   | 0.7   | 0.5   | 0.1   | <1    | 2.05  |
| 1694112                | Rab Sample                       | 4.06 | <0.005 | 1.3   | 5.4   | 17.0  | 12    | 0.3   | 1.3   | 0.8   | 107   | 0.93  | 5.2   | <0.5  | 13.6  | 113   | 0.4   | 0.3   | 0.1   | <1    | 0.99  |
| REP 1694112            | QC                               |      | <0.005 |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| Core Reject Duplicates |                                  |      |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694099                | Rab Sample                       | 3.05 | 0.011  | 0.9   | 2.1   | 13.1  | 10    | 0.2   | 0.7   | 0.1   | 20    | 0.52  | 82.4  | 6.4   | 12.3  | 5     | 0.1   | 0.4   | <0.1  | <1    | 0.02  |
| DUP 1694099            | QC                               |      | 0.015  | 0.8   | 2.0   | 11.5  | 10    | 0.2   | 0.5   | 0.1   | 18    | 0.51  | 72.0  | 10.2  | 10.4  | 4     | 0.1   | 0.4   | <0.1  | <1    | 0.02  |
| 1694133                | Rab Sample                       | 3.83 | <0.005 | 1.5   | 4.5   | 19.3  | 10    | 0.3   | 1.2   | 0.7   | 86    | 0.67  | 4.4   | <0.5  | 13.8  | 96    | 0.4   | 0.6   | 0.2   | <1    | 0.87  |
| DUP 1694133            | QC                               |      | <0.005 | 1.4   | 4.1   | 18.4  | 9     | 0.3   | 1.0   | 0.6   | 83    | 0.64  | 4.4   | <0.5  | 13.6  | 95    | 0.4   | 0.5   | 0.2   | <1    | 0.84  |
| Reference Materials    |                                  |      |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD DS11               | Standard                         |      |        | 13.2  | 137.4 | 129.8 | 337   | 1.6   | 76.2  | 13.3  | 940   | 2.89  | 38.2  | 227.1 | 6.7   | 56    | 2.2   | 6.9   | 11.7  | 44    | 0.98  |
| STD DS11               | Standard                         |      |        | 14.1  | 150.2 | 136.6 | 344   | 1.6   | 78.2  | 13.6  | 1031  | 3.09  | 40.6  | 56.1  | 7.7   | 67    | 2.3   | 8.5   | 11.4  | 48    | 1.06  |
| STD DS11               | Standard                         |      |        | 12.8  | 145.7 | 134.9 | 351   | 1.7   | 72.8  | 12.9  | 967   | 2.88  | 45.7  | 72.1  | 7.3   | 62    | 2.4   | 8.8   | 11.0  | 44    | 0.98  |
| STD OREAS45EA          | Standard                         |      |        | 1.8   | 648.5 | 13.1  | 28    | 0.3   | 360.9 | 44.3  | 402   | 21.79 | 11.2  | 55.4  | 9.7   | 3     | <0.1  | 0.5   | 0.2   | 296   | 0.03  |
| STD OREAS45EA          | Standard                         |      |        | 1.7   | 706.7 | 14.3  | 34    | 0.2   | 395.5 | 54.5  | 404   | 21.78 | 11.5  | 54.6  | 10.5  | 4     | <0.1  | 0.4   | 0.3   | 313   | 0.04  |
| STD OREAS45EA          | Standard                         |      |        | 1.8   | 670.3 | 14.4  | 31    | 0.2   | 380.4 | 51.2  | 385   | 19.71 | 11.6  | 60.3  | 10.1  | 4     | <0.1  | 0.5   | 0.3   | 287   | 0.03  |
| STD OXC145             | Standard                         |      | 0.208  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXC145             | Standard                         |      | 0.208  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXH139             | Standard                         |      | 1.326  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXH139             | Standard                         |      | 1.299  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134             | Standard                         |      | 7.849  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134             | Standard                         |      | 7.652  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134 Expected    |                                  |      | 7.667  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXC145 Expected    |                                  |      | 0.212  |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |





**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

**White Gold Corp.**

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

BZA

Report Date:

July 26, 2018

Page:

1 of 2

Part:

2 of 2

## QUALITY CONTROL REPORT

WHI18000213.1

|                        | Method<br>Analyte<br>Unit<br>MDL | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|------------------------|----------------------------------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|                        |                                  | P     | La    | Cr    | Mg    | Ba    | Ti     | B     | Al    | Na    | K     | W     | Hg    | Sc    | Tl    | S     | Ga    | Se    | Te    |
|                        |                                  | %     | ppm   | ppm   | %     | ppm   | %      | ppm   | %     | %     | %     | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppm   | ppm   |
|                        |                                  | 0.001 | 1     | 1     | 0.01  | 1     | 0.001  | 20    | 0.01  | 0.001 | 0.01  | 0.1   | 0.01  | 0.1   | 0.1   | 0.05  | 1     | 0.5   | 0.2   |
| Pulp Duplicates        |                                  |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694076                | Rab Sample                       | 0.005 | 30    | 2     | 0.01  | 162   | <0.001 | <20   | 0.22  | 0.019 | 0.24  | 0.8   | 0.04  | 0.8   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| REP 1694076            | QC                               | 0.004 | 34    | 3     | 0.01  | 176   | <0.001 | <20   | 0.22  | 0.020 | 0.25  | 0.8   | 0.05  | 0.8   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| 1694110                | Rab Sample                       | 0.005 | 40    | 5     | 0.04  | 745   | 0.001  | <20   | 0.38  | 0.015 | 0.27  | 1.1   | 0.02  | 2.5   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| REP 1694110            | QC                               |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694111                | Rab Sample                       | 0.005 | 40    | 5     | 0.04  | 1064  | <0.001 | <20   | 0.31  | 0.015 | 0.24  | 1.4   | 0.05  | 4.0   | 0.1   | 0.08  | <1    | <0.5  | <0.2  |
| REP 1694111            | QC                               | 0.005 | 42    | 6     | 0.04  | 1079  | <0.001 | <20   | 0.33  | 0.016 | 0.24  | 1.4   | 0.04  | 4.0   | <0.1  | 0.08  | 1     | <0.5  | <0.2  |
| 1694112                | Rab Sample                       | 0.005 | 41    | 8     | 0.03  | 770   | <0.001 | <20   | 0.37  | 0.028 | 0.24  | 1.9   | 0.05  | 2.9   | 0.1   | 0.10  | 1     | <0.5  | <0.2  |
| REP 1694112            | QC                               |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| Core Reject Duplicates |                                  |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| 1694099                | Rab Sample                       | 0.004 | 28    | 3     | <0.01 | 139   | <0.001 | <20   | 0.23  | 0.015 | 0.18  | 0.6   | 0.02  | 0.8   | <0.1  | <0.05 | 1     | <0.5  | <0.2  |
| DUP 1694099            | QC                               | 0.004 | 29    | 3     | <0.01 | 111   | <0.001 | <20   | 0.22  | 0.014 | 0.18  | 0.4   | 0.01  | 0.7   | <0.1  | <0.05 | <1    | <0.5  | <0.2  |
| 1694133                | Rab Sample                       | 0.006 | 45    | 6     | 0.03  | 784   | 0.002  | <20   | 0.35  | 0.017 | 0.28  | 3.3   | <0.01 | 2.8   | 0.1   | 0.07  | 1     | <0.5  | <0.2  |
| DUP 1694133            | QC                               | 0.005 | 45    | 6     | 0.03  | 763   | 0.002  | <20   | 0.33  | 0.016 | 0.27  | 3.3   | <0.01 | 2.7   | 0.1   | 0.07  | 1     | <0.5  | <0.2  |
| Reference Materials    |                                  |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD DS11               | Standard                         | 0.068 | 15    | 51    | 0.78  | 344   | 0.077  | <20   | 1.03  | 0.068 | 0.37  | 2.8   | 0.26  | 2.6   | 4.7   | 0.26  | 5     | 2.2   | 4.2   |
| STD DS11               | Standard                         | 0.068 | 19    | 56    | 0.83  | 403   | 0.093  | <20   | 1.18  | 0.074 | 0.41  | 2.9   | 0.24  | 3.3   | 5.0   | 0.28  | 5     | 2.7   | 4.5   |
| STD DS11               | Standard                         | 0.068 | 17    | 55    | 0.78  | 363   | 0.082  | <20   | 1.02  | 0.067 | 0.38  | 3.2   | 0.22  | 2.9   | 4.8   | 0.26  | 5     | 1.9   | 4.6   |
| STD OREAS45EA          | Standard                         | 0.028 | 6     | 796   | 0.08  | 137   | 0.084  | <20   | 2.90  | 0.018 | 0.05  | <0.1  | <0.01 | 73.5  | <0.1  | <0.05 | 12    | 1.1   | <0.2  |
| STD OREAS45EA          | Standard                         | 0.033 | 7     | 849   | 0.11  | 141   | 0.089  | <20   | 3.42  | 0.015 | 0.06  | <0.1  | 0.02  | 80.6  | <0.1  | <0.05 | 13    | 1.7   | <0.2  |
| STD OREAS45EA          | Standard                         | 0.029 | 7     | 820   | 0.10  | 150   | 0.091  | <20   | 3.15  | 0.017 | 0.05  | <0.1  | <0.01 | 77.1  | <0.1  | <0.05 | 12    | 1.3   | <0.2  |
| STD OXC145             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXC145             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXH139             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXH139             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134             | Standard                         |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXN134 Expected    |                                  |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OXC145 Expected    |                                  |       |       |       |       |       |        |       |       |       |       |       |       |       |       |       |       |       |       |



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 2

**Part:** 1 of 2

## QUALITY CONTROL REPORT

WHI18000213.1

|                        |            | WGHT   | FA430  | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|------------------------|------------|--------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|                        |            | Wgt    | Au     | Mo    | Cu    | Pb    | Zn    | Ag    | Ni    | Co    | Mn    | Fe    | As    | Au    | Th    | Sr    | Cd    | Sb    | Bi    | V     | Ca    |
|                        |            | kg     | ppm    | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     | ppm   | ppb   | ppm   | ppm   | ppm   | ppm   | ppm   | ppm   | %     |
|                        |            | 0.01   | 0.005  | 0.1   | 0.1   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     | 0.01  | 0.5   | 0.5   | 0.1   | 1     | 0.1   | 0.1   | 0.1   | 1     | 0.01  |
| STD OXH139 Expected    |            | 1.312  |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| STD OREAS45EA Expected |            |        |        | 1.6   | 709   | 14.3  | 31.4  | 0.26  | 381   | 52    | 400   | 22.65 | 11.4  | 53    | 10.7  | 4.05  | 0.03  | 0.32  | 0.26  | 303   | 0.036 |
| STD DS11 Expected      |            |        |        | 13.9  | 149   | 138   | 345   | 1.71  | 77.7  | 14.2  | 1055  | 3.1   | 42.8  | 79    | 7.65  | 67.3  | 2.37  | 7.2   | 12.2  | 50    | 1.063 |
| BLK                    | Blank      | <0.005 |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| BLK                    | Blank      | <0.005 |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| BLK                    | Blank      | <0.005 |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| BLK                    | Blank      | 0.005  |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| BLK                    | Blank      |        |        | <0.1  | <0.1  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 | <0.5  | <0.5  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 |
| BLK                    | Blank      |        |        | <0.1  | <0.1  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 | <0.5  | <0.5  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 |
| BLK                    | Blank      |        |        | <0.1  | <0.1  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 | <0.5  | <0.5  | <0.1  | <1    | <0.1  | <0.1  | <0.1  | <1    | <0.01 |
| Prep Wash              |            |        |        |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
| ROCK-WHI               | Prep Blank |        | <0.005 | 1.4   | 6.0   | 1.0   | 36    | <0.1  | 0.7   | 3.3   | 473   | 1.57  | 1.0   | <0.5  | 1.9   | 23    | <0.1  | <0.1  | <0.1  | 18    | 0.58  |
| ROCK-WHI               | Prep Blank |        | <0.005 | 1.0   | 4.5   | 1.0   | 30    | <0.1  | 1.1   | 3.3   | 510   | 1.56  | 1.0   | 2.0   | 1.8   | 21    | <0.1  | <0.1  | <0.1  | 19    | 0.58  |



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 2

**Part:** 2 of 2

## QUALITY CONTROL REPORT

WHI18000213.1

|                        |            | AQ200<br>P<br>%<br>0.001 | AQ200<br>La<br>ppm<br>1 | AQ200<br>Cr<br>ppm<br>1 | AQ200<br>Mg<br>%<br>0.01 | AQ200<br>Ba<br>ppm<br>1 | AQ200<br>Ti<br>%<br>0.001 | AQ200<br>B<br>ppm<br>20 | AQ200<br>Al<br>%<br>0.01 | AQ200<br>Na<br>%<br>0.001 | AQ200<br>K<br>%<br>0.01 | AQ200<br>W<br>ppm<br>0.1 | AQ200<br>Hg<br>ppm<br>0.01 | AQ200<br>Sc<br>ppm<br>0.1 | AQ200<br>Tl<br>ppm<br>0.1 | AQ200<br>S<br>%<br>0.05 | AQ200<br>Ga<br>ppm<br>1 | AQ200<br>Se<br>ppm<br>0.5 | AQ200<br>Te<br>ppm<br>0.2 |
|------------------------|------------|--------------------------|-------------------------|-------------------------|--------------------------|-------------------------|---------------------------|-------------------------|--------------------------|---------------------------|-------------------------|--------------------------|----------------------------|---------------------------|---------------------------|-------------------------|-------------------------|---------------------------|---------------------------|
| STD OXH139 Expected    |            |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| STD OREAS45EA Expected |            | 0.029                    | 7.06                    | 849                     | 0.095                    | 148                     | 0.0984                    |                         | 3.32                     | 0.02                      | 0.053                   |                          |                            | 78                        | 0.072                     | 0.036                   | 12.4                    | 0.78                      | 0.1                       |
| STD DS11 Expected      |            | 0.0701                   | 18.6                    | 61.5                    | 0.85                     | 417                     | 0.0976                    |                         | 1.129                    | 0.0694                    | 0.4                     | 2.9                      | 0.26                       | 3.1                       | 4.9                       | 0.2835                  | 4.7                     | 2.2                       | 4.56                      |
| BLK                    | Blank      |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| BLK                    | Blank      |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| BLK                    | Blank      |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| BLK                    | Blank      |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| BLK                    | Blank      | <0.001                   | <1                      | <1                      | <0.01                    | <1                      | <0.001                    | <20                     | <0.01                    | <0.001                    | <0.01                   | <0.1                     | <0.01                      | 0.1                       | <0.1                      | <0.05                   | <1                      | <0.5                      | <0.2                      |
| BLK                    | Blank      | <0.001                   | <1                      | <1                      | <0.01                    | <1                      | <0.001                    | <20                     | <0.01                    | <0.001                    | <0.01                   | <0.1                     | <0.01                      | <0.1                      | <0.1                      | <0.05                   | <1                      | <0.5                      | <0.2                      |
| BLK                    | Blank      | <0.001                   | <1                      | <1                      | <0.01                    | <1                      | <0.001                    | <20                     | <0.01                    | <0.001                    | <0.01                   | <0.1                     | <0.01                      | <0.1                      | <0.1                      | <0.05                   | <1                      | <0.5                      | <0.2                      |
| Prep Wash              |            |                          |                         |                         |                          |                         |                           |                         |                          |                           |                         |                          |                            |                           |                           |                         |                         |                           |                           |
| ROCK-WHI               | Prep Blank | 0.039                    | 5                       | 2                       | 0.46                     | 54                      | 0.057                     | <20                     | 0.81                     | 0.052                     | 0.07                    | <0.1                     | <0.01                      | 2.3                       | <0.1                      | <0.05                   | 3                       | <0.5                      | <0.2                      |
| ROCK-WHI               | Prep Blank | 0.039                    | 5                       | 3                       | 0.48                     | 53                      | 0.068                     | <20                     | 0.83                     | 0.068                     | 0.08                    | <0.1                     | <0.01                      | 2.3                       | <0.1                      | <0.05                   | 4                       | <0.5                      | <0.2                      |