



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 1  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

**CERTIFICATE VA18266880**

Project: TA22-04-YUK8

This report is for 171 Pulp samples submitted to our lab in Vancouver, BC, Canada on 22-OCT-2018.

The following have access to data associated with this certificate:

CHAD ULANSKY

**SAMPLE PREPARATION**

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-24	Pulp Login - Rcd w/o Barcode
LOG-QC	QC Test on Received Samples

**ANALYTICAL PROCEDURES**

ALS CODE	DESCRIPTION	
Pb-OG62	Ore Grade Pb - Four Acid	
Zn-OG62	Ore Grade Zn - Four Acid	
Au-ICP22	Au 50g FA ICP-AES finish	ICP-AES
ME-MS61	48 element four acid ICP-MS	
ME-OG62	Ore Grade Elements - Four Acid	ICP-AES

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

\*\*\*\*\* See Appendix Page for comments regarding this certificate \*\*\*\*\*

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 2 - A  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
18-8543-3		0.28	0.77	5.62	15.6	560	2.07	0.27	0.24	2.69	66.5	15.3	192	5.79	44.5	3.85
18-8543-4		0.28	0.55	6.35	4.5	540	2.73	0.21	0.10	1.63	76.0	14.1	201	7.43	29.2	3.05
18-8543-5		0.28	1.27	6.34	24.9	540	2.06	1.00	0.27	2.93	60.9	27.3	205	5.25	79.0	4.85
18-8543-6		0.28	0.83	6.06	86.9	500	2.25	0.96	0.13	1.24	64.8	30.6	129	6.37	98.2	4.36
18-8543-7		0.26	0.67	5.90	57.7	490	2.17	0.81	0.09	0.87	65.0	29.2	140	6.10	66.7	4.05
18-8543-8		0.26	0.57	6.14	69.2	520	2.31	1.44	0.10	0.56	68.3	25.9	154	6.06	48.7	3.96
18-8543-9		0.28	0.40	6.44	42.9	550	2.10	0.55	0.12	0.64	66.9	18.6	173	6.22	47.1	3.69
18-8543-10		0.30	0.01	0.43	0.2	20	0.12	0.01	<0.01	<0.02	15.00	0.8	344	0.31	3.5	0.41
18-8543-11		0.30	1.47	5.81	228	500	2.05	1.77	0.10	4.41	66.0	34.2	160	5.95	174.5	5.37
18-8543-12		0.28	1.05	5.31	62.2	530	2.11	0.76	0.15	3.80	63.4	52.3	172	5.10	78.3	6.18
18-8543-13		0.26	1.54	6.09	51.2	580	2.18	0.60	0.11	3.32	67.9	22.4	157	5.55	82.5	5.57
18-8543-14		0.26	1.59	6.22	236	290	1.84	2.56	0.06	7.30	54.2	21.2	149	5.57	119.0	6.17
18-8543-15		0.26	1.89	6.22	365	490	2.26	2.70	0.18	8.27	72.1	24.7	154	6.34	155.5	5.87
18-8543-16		0.26	0.12	6.21	10.8	560	2.58	0.46	0.08	0.28	75.7	25.7	137	7.17	46.3	3.61
18-8543-17		0.26	0.26	6.50	19.6	540	2.51	0.38	0.68	1.00	75.0	20.2	171	6.52	34.6	3.20
18-8543-18		0.28	0.11	6.80	10.1	500	2.57	0.22	0.09	0.48	74.4	12.0	112	5.97	17.1	3.39
18-8543-19		0.26	0.14	6.95	19.2	510	2.84	0.22	0.06	1.17	75.9	12.3	122	5.89	21.7	2.88
18-8543-20		0.26	0.12	6.80	12.5	490	2.72	0.17	0.05	0.70	73.1	12.5	115	5.55	17.9	2.99
18-8543-21		0.22	0.01	0.49	0.3	20	0.12	0.01	<0.01	<0.02	16.95	1.0	419	0.34	3.9	0.52
18-8543-22		0.06	69.0	5.32	85.8	100	1.68	4.05	1.94	281	37.9	30.8	37	3.32	3610	3.61
18-8544-1		0.30	1.64	5.90	24.1	510	2.38	0.56	0.47	2.42	66.9	22.9	169	5.57	73.5	3.77
18-8544-2		0.28	0.91	5.30	35.2	510	1.93	1.52	1.16	6.01	67.8	16.9	183	4.54	45.8	4.30
18-8544-3		0.26	0.25	5.45	32.3	610	1.96	0.60	0.95	3.43	68.0	22.8	216	4.24	42.3	4.02
18-8544-4		0.26	0.10	6.03	19.2	550	2.11	0.31	0.24	0.79	67.9	12.3	227	4.77	31.6	3.22
18-8544-5		0.28	0.22	5.87	27.7	490	1.61	0.70	0.28	0.71	65.5	17.8	256	5.29	85.7	4.46
18-8544-6		0.28	0.20	5.60	25.9	520	1.67	0.73	0.56	0.50	63.7	20.9	301	4.16	62.9	4.24
18-8544-7		0.28	0.14	5.35	16.9	590	1.70	0.27	0.71	0.50	65.6	15.2	321	3.09	23.7	3.39
18-8544-8		0.28	0.18	5.42	20.0	600	1.72	0.33	0.56	0.53	66.7	16.8	240	3.32	29.1	3.73
18-8544-9		0.28	0.42	5.36	22.9	580	1.43	0.38	0.34	0.59	64.3	17.1	261	3.36	32.6	3.95
18-8544-10		0.28	0.55	5.41	26.1	640	1.55	0.47	0.62	1.14	60.1	19.1	243	3.73	55.3	4.14
18-8544-11		0.28	0.48	5.51	17.6	650	1.74	0.35	0.33	0.87	61.1	14.7	219	3.66	52.4	3.33
18-8544-12		0.28	0.01	0.49	0.2	20	0.15	0.01	0.01	<0.02	14.35	0.9	379	0.30	3.3	0.48
18-8544-13		0.28	0.77	5.84	38.6	620	1.79	0.50	0.31	1.84	65.4	22.2	306	4.41	71.5	3.92
18-8544-14		0.28	1.82	4.86	268	370	1.39	3.47	0.20	15.60	53.8	8.3	200	2.88	119.0	7.64
18-8544-15		0.28	0.86	6.32	8.7	500	2.13	0.64	0.16	1.18	67.3	28.2	176	6.02	75.7	4.39
18-8544-16		0.28	0.08	5.04	11.9	260	1.74	0.38	5.27	0.12	61.9	13.2	74	2.53	13.9	2.88
18-8544-17		0.28	0.09	5.14	9.5	350	1.68	0.30	5.22	0.16	60.9	12.4	106	2.65	12.8	2.87
18-8544-18		0.30	0.06	4.54	8.7	310	1.30	0.23	7.03	0.06	57.2	10.9	53	1.96	10.8	2.41
18-8544-19		0.26	0.07	3.93	11.7	240	1.13	0.18	9.44	0.06	46.2	12.0	39	2.26	22.3	2.03
18-8544-20		0.28	0.15	5.72	12.2	490	1.57	0.35	0.60	0.93	66.1	13.9	163	3.15	15.4	3.64



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 2 - B  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		ppm 0.05	ppm 0.05	ppm 0.1	ppm 0.005	% 0.01	ppm 0.5	ppm 0.2	% 0.01	ppm 5	ppm 0.05	% 0.01	ppm 0.1	ppm 0.2	ppm 10
18-8543-3		13.95	0.19	2.0	0.079	3.28	29.1	31.8	1.05	2880	1.03	0.12	6.9	27.2	340
18-8543-4		17.85	0.20	2.4	0.058	3.71	33.6	45.1	1.14	910	1.31	0.06	9.4	27.9	360
18-8543-5		16.65	0.18	2.0	0.107	2.97	26.3	43.4	1.43	2050	1.30	0.09	7.1	37.9	410
18-8543-6		15.70	0.19	2.0	0.052	3.32	28.5	53.2	1.61	846	1.50	0.16	6.3	42.4	320
18-8543-7		15.80	0.18	2.1	0.046	3.12	28.9	53.1	1.48	765	1.78	0.16	6.8	43.2	290
18-8543-8		16.25	0.18	2.3	0.052	3.20	30.1	54.3	1.42	895	1.95	0.20	8.0	40.4	300
18-8543-9		15.80	0.19	2.2	0.036	3.30	29.4	54.9	1.97	659	1.57	0.24	8.2	34.2	330
18-8543-10		1.31	0.08	0.1	<0.005	0.20	6.2	2.3	0.02	31	0.90	0.01	1.0	6.0	20
18-8543-11		15.50	0.19	2.0	0.070	3.13	29.2	48.8	1.34	1550	2.59	0.14	5.9	48.8	330
18-8543-12		13.35	0.18	2.2	0.050	3.15	27.8	41.1	0.72	1100	5.64	0.08	4.9	76.1	360
18-8543-13		16.55	0.20	2.2	0.097	3.18	30.7	42.7	1.63	928	1.89	0.12	4.6	35.6	340
18-8543-14		16.05	0.18	1.6	0.076	3.05	23.9	29.5	0.84	2770	1.04	0.04	3.1	35.8	390
18-8543-15		17.60	0.21	2.1	0.101	3.62	32.1	46.9	1.12	2850	1.35	0.07	4.8	44.4	390
18-8543-16		17.40	0.20	2.4	0.051	3.86	33.6	61.9	1.31	496	1.55	0.08	8.5	40.5	330
18-8543-17		17.55	0.20	2.3	0.060	4.08	33.6	63.2	1.56	728	1.28	0.07	8.5	34.5	390
18-8543-18		18.50	0.21	2.7	0.049	3.56	32.4	63.1	2.01	574	0.68	0.04	9.0	27.8	330
18-8543-19		18.00	0.23	2.3	0.051	4.14	33.5	55.4	0.91	702	0.89	0.06	8.6	25.2	330
18-8543-20		18.05	0.21	2.3	0.045	3.83	32.3	56.4	1.00	483	0.80	0.05	8.2	26.0	330
18-8543-21		1.54	0.10	0.2	<0.005	0.23	7.2	2.9	0.02	36	1.17	0.01	1.2	7.2	20
18-8543-22		24.9	0.17	4.3	1.855	2.05	15.4	14.8	0.42	523	14.10	1.29	10.0	27.1	380
18-8544-1		15.60	0.20	2.1	0.105	3.41	29.9	34.9	1.08	1570	2.32	0.07	7.6	34.9	350
18-8544-2		13.35	0.20	1.8	0.081	3.17	29.6	21.4	0.99	3240	1.18	0.09	6.4	24.9	350
18-8544-3		14.30	0.20	1.9	0.104	3.29	29.2	23.3	0.92	4780	1.20	0.16	7.3	35.0	460
18-8544-4		14.80	0.18	2.1	0.062	3.63	29.2	22.3	0.81	2270	0.86	0.08	8.0	24.1	290
18-8544-5		14.55	0.10	2.1	0.089	3.21	32.2	23.9	0.89	3940	1.44	0.11	6.8	31.1	330
18-8544-6		13.70	0.10	2.0	0.083	3.18	30.6	22.5	0.99	4010	1.32	0.14	6.2	30.6	300
18-8544-7		13.50	0.08	1.8	0.073	3.29	32.0	20.8	0.68	4400	1.05	0.13	6.8	29.0	280
18-8544-8		13.60	0.09	1.9	0.095	3.23	32.7	21.6	0.61	4590	0.90	0.17	6.5	27.6	370
18-8544-9		13.45	0.07	1.8	0.092	3.21	31.5	23.0	0.55	4790	1.46	0.14	6.8	28.2	390
18-8544-10		13.45	0.09	1.9	0.115	3.11	30.0	23.5	0.71	4460	1.22	0.24	6.6	30.7	520
18-8544-11		13.65	0.08	1.9	0.074	3.54	29.9	25.3	0.79	3200	0.97	0.12	6.2	27.9	370
18-8544-12		1.46	0.06	0.1	0.009	0.22	6.9	2.6	0.02	40	0.82	0.01	1.1	5.6	30
18-8544-13		14.40	0.11	2.2	0.092	3.36	32.6	27.8	1.02	3510	1.90	0.14	7.0	34.3	370
18-8544-14		11.95	0.08	1.6	0.235	2.43	26.4	18.4	0.67	7020	1.34	0.12	3.8	18.8	320
18-8544-15		16.30	0.07	2.2	0.056	3.26	34.2	42.5	1.36	1180	1.90	0.12	7.3	41.8	380
18-8544-16		13.15	0.09	1.8	0.063	3.29	31.6	46.9	3.60	2010	0.39	0.07	7.1	23.7	620
18-8544-17		13.70	0.09	1.9	0.060	3.62	30.3	48.1	3.18	1640	0.59	0.09	7.9	23.6	630
18-8544-18		12.50	0.08	1.8	0.045	3.25	29.0	42.1	5.09	1230	0.22	0.05	7.9	21.4	580
18-8544-19		10.10	0.07	1.6	0.045	2.57	22.4	34.4	6.27	1380	0.22	0.04	6.0	15.6	500
18-8544-20		15.35	0.09	1.9	0.064	3.28	30.6	59.7	1.93	3450	0.58	0.12	7.7	31.2	410



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 2 - C  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Ti	U	V
		ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005	0.02	0.1	1
18-8543-3		137.5	<0.002	0.04	3.35	9.4	<1	1.6	23.1	0.48	<0.05	9.67	0.229	0.60	1.7	60
18-8543-4		164.0	<0.002	0.03	4.15	12.4	1	2.1	17.5	0.64	<0.05	11.50	0.279	0.72	1.9	72
18-8543-5		123.0	0.002	0.02	4.09	16.5	1	1.8	18.8	0.47	0.10	9.29	0.306	0.59	1.8	108
18-8543-6		139.5	<0.002	0.10	7.18	11.7	1	1.8	17.8	0.44	0.05	9.89	0.231	0.75	2.0	74
18-8543-7		137.5	<0.002	0.08	6.21	11.1	1	1.7	16.8	0.46	<0.05	10.15	0.228	0.76	2.1	68
18-8543-8		150.5	<0.002	0.05	8.87	11.2	<1	1.9	18.9	0.56	<0.05	10.50	0.256	0.78	2.1	69
18-8543-9		144.0	<0.002	0.07	3.99	10.8	1	1.8	17.4	0.59	<0.05	10.40	0.271	0.80	1.9	71
18-8543-10		5.2	<0.002	<0.01	0.21	0.7	<1	0.3	5.6	0.05	<0.05	2.24	0.036	0.03	0.3	6
18-8543-11		139.0	<0.002	0.07	9.74	11.7	1	1.7	17.5	0.40	0.06	9.84	0.215	0.80	2.3	78
18-8543-12		131.5	<0.002	0.07	11.90	8.6	1	1.4	20.0	0.35	0.13	10.15	0.177	0.94	2.6	60
18-8543-13		125.0	<0.002	0.12	5.66	11.7	1	1.8	19.5	0.30	0.05	10.25	0.173	0.63	2.3	81
18-8543-14		135.5	<0.002	0.01	7.38	16.5	1	1.3	12.8	0.21	<0.05	7.21	0.177	0.58	1.9	132
18-8543-15		146.5	<0.002	0.02	7.91	13.8	1	1.9	19.2	0.32	0.06	10.35	0.174	0.77	2.3	83
18-8543-16		151.0	<0.002	0.05	2.01	11.5	1	2.1	20.0	0.62	0.07	11.60	0.253	0.79	2.2	64
18-8543-17		154.5	<0.002	0.04	2.77	11.2	1	2.1	17.8	0.60	0.05	11.10	0.260	0.72	2.1	66
18-8543-18		151.5	<0.002	0.01	1.58	12.0	1	2.2	12.4	0.65	<0.05	11.10	0.266	0.70	2.1	68
18-8543-19		167.5	<0.002	0.01	2.09	11.6	1	2.1	16.0	0.61	<0.05	11.40	0.260	0.65	2.1	68
18-8543-20		166.0	<0.002	0.01	2.00	11.6	1	2.0	11.7	0.59	<0.05	10.95	0.257	0.64	2.2	70
18-8543-21		6.0	<0.002	<0.01	0.26	0.8	<1	0.4	6.2	0.06	<0.05	2.53	0.042	0.03	0.3	7
18-8543-22		66.2	<0.002	4.58	144.5	5.8	5	5.0	93.9	0.73	0.06	5.94	0.156	2.03	2.7	32
18-8544-1		147.0	<0.002	0.04	6.02	11.0	1	1.8	17.2	0.54	0.06	10.35	0.244	0.60	1.9	73
18-8544-2		137.5	<0.002	0.04	5.92	8.5	1	1.6	30.3	0.44	0.10	10.00	0.197	0.51	3.4	40
18-8544-3		138.0	<0.002	0.03	2.49	9.2	1	1.7	32.5	0.50	0.06	10.25	0.223	0.56	1.7	48
18-8544-4		157.5	<0.002	0.01	1.80	9.0	<1	1.8	16.8	0.56	<0.05	11.15	0.235	0.54	1.7	46
18-8544-5		149.5	<0.002	0.02	2.27	9.4	<1	1.8	25.6	0.47	0.09	12.05	0.218	0.56	1.8	47
18-8544-6		134.5	<0.002	0.02	1.99	8.2	<1	1.6	25.6	0.42	0.09	11.10	0.199	0.51	1.6	43
18-8544-7		141.5	<0.002	0.02	1.61	8.1	<1	1.7	21.2	0.49	<0.05	10.55	0.209	0.54	1.4	43
18-8544-8		141.5	<0.002	0.02	1.89	8.7	<1	1.6	24.0	0.48	0.05	10.85	0.217	0.56	1.5	46
18-8544-9		139.0	<0.002	0.02	2.60	8.4	1	1.7	24.0	0.50	<0.05	10.60	0.213	0.55	1.8	46
18-8544-10		133.5	<0.002	0.03	2.53	9.1	1	1.7	37.0	0.48	<0.05	10.90	0.224	0.58	1.8	54
18-8544-11		141.5	<0.002	0.02	2.28	9.1	<1	1.6	20.2	0.46	0.08	10.50	0.216	0.59	1.4	54
18-8544-12		5.6	<0.002	<0.01	0.22	0.8	<1	0.3	5.8	0.05	<0.05	2.59	0.042	0.04	0.3	6
18-8544-13		141.0	<0.002	0.02	3.72	9.4	<1	1.8	26.9	0.49	0.07	11.25	0.230	0.61	1.8	51
18-8544-14		108.5	<0.002	0.02	10.65	7.0	1	2.1	99.2	0.27	<0.05	9.42	0.142	0.47	2.8	37
18-8544-15		147.5	<0.002	0.06	4.59	10.6	<1	2.0	17.2	0.53	<0.05	11.55	0.255	0.68	2.1	68
18-8544-16		107.0	<0.002	0.02	1.29	9.2	<1	2.2	22.4	0.53	<0.05	9.27	0.226	0.39	1.3	47
18-8544-17		110.0	<0.002	0.02	1.21	9.2	1	1.8	30.7	0.57	<0.05	9.62	0.240	0.48	1.4	47
18-8544-18		92.6	<0.002	0.01	1.09	8.3	<1	1.7	25.5	0.55	<0.05	8.98	0.223	0.36	1.3	40
18-8544-19		72.6	<0.002	<0.01	1.22	6.7	<1	1.4	28.1	0.45	0.07	7.54	0.184	0.34	1.1	33
18-8544-20		108.5	<0.002	0.02	1.76	9.3	<1	1.9	22.2	0.55	<0.05	9.70	0.246	0.56	1.7	62



ALS Canada Ltd.  
2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 2 - D  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Pb-OG62 Pb % 0.001	Zn-OG62 Zn % 0.001	Au-ICP22 Au ppm 0.001
18-8543-3		0.9	10.8	809	68.9			<0.001
18-8543-4		1.1	9.2	618	79.1			<0.001
18-8543-5		1.4	11.1	1470	73.3			<0.001
18-8543-6		1.1	8.6	591	72.7			0.001
18-8543-7		1.1	8.6	417	73.0			0.001
18-8543-8		1.1	9.9	228	81.4			0.003
18-8543-9		1.0	8.7	270	76.3			<0.001
18-8543-10		0.2	1.3	<2	4.3			<0.001
18-8543-11		1.2	9.8	1520	73.2			0.002
18-8543-12		0.9	11.7	1780	79.5			0.006
18-8543-13		0.9	7.9	1500	85.4			0.003
18-8543-14		1.7	8.8	2360	54.7			<0.001
18-8543-15		1.7	11.4	2190	72.7			0.001
18-8543-16		1.4	10.2	146	85.7			<0.001
18-8543-17		1.5	11.2	356	80.4			<0.001
18-8543-18		1.3	9.2	232	86.1			<0.001
18-8543-19		1.4	8.8	490	79.3			<0.001
18-8543-20		1.3	8.3	277	77.7			<0.001
18-8543-21		0.1	1.5	2	5.4			<0.001
18-8543-22		2.5	9.7	>10000	160.0	1.355	5.28	1.255
18-8544-1		1.0	9.4	1400	71.7			0.005
18-8544-2		1.0	11.9	1540	65.5			<0.001
18-8544-3		0.9	16.3	1200	70.9			0.001
18-8544-4		1.1	10.6	306	72.2			<0.001
18-8544-5		1.1	13.8	249	73.9			<0.001
18-8544-6		0.9	14.1	241	69.9			<0.001
18-8544-7		0.9	15.3	217	62.8			0.001
18-8544-8		0.8	17.6	250	65.4			0.001
18-8544-9		0.9	15.8	266	66.5			<0.001
18-8544-10		0.9	17.3	464	66.3			0.001
18-8544-11		0.9	12.3	459	62.1			<0.001
18-8544-12		0.1	1.3	3	5.1			<0.001
18-8544-13		1.1	12.2	1010	78.1			<0.001
18-8544-14		1.8	7.0	4450	51.1			<0.001
18-8544-15		1.0	8.9	680	84.3			0.001
18-8544-16		1.2	21.1	66	62.3			0.001
18-8544-17		1.2	20.7	67	64.5			0.002
18-8544-18		1.2	16.9	46	62.6			<0.001
18-8544-19		1.1	15.5	59	51.1			<0.001
18-8544-20		1.2	18.6	249	65.2			0.003



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 3 - A  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
18-8544-21		0.24	0.01	0.49	0.4	20	0.11	0.01	0.01	<0.02	14.45	0.8	420	0.31	3.7	0.49
18-8544-22		0.06	64.8	5.63	74.4	110	1.60	3.86	1.90	267	39.5	27.4	37	3.09	3450	3.52
18-8545-1		0.26	0.21	0.84	10.2	80	0.47	0.08	17.20	0.35	11.10	2.1	37	0.51	87.1	1.38
18-8545-2		0.30	0.01	0.48	0.3	20	0.10	0.01	0.03	0.03	14.85	0.8	379	0.31	3.6	0.44
18-8545-3		0.26	0.04	4.56	10.6	240	1.29	0.28	7.14	0.07	54.0	11.7	72	2.42	18.4	2.24
18-8545-4		0.26	0.10	2.88	9.6	160	0.95	0.41	11.20	0.16	27.2	6.2	42	1.56	15.3	1.83
18-8545-5		0.24	0.05	3.05	8.2	120	0.81	0.26	11.05	0.08	35.5	4.4	30	1.27	5.3	1.99
18-8545-6		0.28	0.14	5.49	12.1	530	1.76	0.44	0.45	0.64	61.4	11.8	194	3.50	17.3	3.89
18-8545-7		0.28	0.16	5.32	16.1	380	1.58	0.48	3.23	0.63	56.6	13.4	172	3.20	17.5	3.31
18-8545-8		0.28	0.12	3.98	11.0	220	1.12	0.48	8.43	0.23	44.0	8.9	89	2.06	13.6	2.66
18-8545-9		0.28	0.14	3.65	12.4	180	1.15	0.51	9.19	0.20	39.2	8.0	55	1.85	12.9	2.73
18-8545-10		0.30	0.22	3.84	13.3	190	1.17	0.42	8.17	0.37	39.9	8.8	89	2.41	17.2	2.91
18-8545-11		0.30	0.23	3.37	11.7	190	0.96	0.33	9.42	0.46	35.3	8.6	69	2.16	12.6	2.58
18-8545-12		0.30	0.24	2.92	12.4	170	0.75	0.28	11.05	0.54	33.7	7.0	46	1.88	11.4	2.15
18-8545-13		0.30	0.13	2.89	10.5	160	0.78	0.33	11.40	0.29	32.0	6.2	37	1.60	10.2	1.99
18-8545-14		0.34	0.17	2.29	12.0	100	0.67	0.43	12.45	0.23	23.7	5.2	68	1.34	11.5	2.03
18-8545-15		0.28	0.09	2.50	8.1	100	0.78	0.33	12.40	0.12	26.3	4.4	45	1.30	7.9	1.80
18-8545-16		0.26	0.11	2.65	8.2	110	0.74	0.31	12.40	0.14	25.8	4.3	47	1.44	8.5	1.89
18-8545-17		0.26	0.36	3.05	14.5	120	1.01	0.46	11.85	0.27	29.0	5.8	42	1.84	13.2	2.08
18-8545-18		0.28	0.16	3.65	12.7	160	1.08	0.36	10.30	0.15	40.2	6.5	45	2.12	12.7	2.20
18-8545-19		0.30	0.16	2.69	13.0	100	1.08	0.39	13.85	0.17	28.8	5.9	33	1.68	17.0	2.12
18-8545-20		0.30	0.11	2.92	9.7	120	0.78	0.35	12.25	0.10	26.7	4.9	33	1.27	16.8	1.90
18-8545-21		0.24	0.01	0.49	0.6	20	0.09	0.01	0.02	<0.02	15.15	0.9	391	0.31	3.9	0.50
18-8545-22		0.06	68.1	5.76	81.3	140	1.77	4.09	1.98	279	38.8	28.7	39	3.13	3660	3.68
18-8546-1		0.28	0.30	0.96	9.4	60	0.43	0.06	18.60	0.71	9.91	3.1	32	0.48	12.5	1.42
18-8546-2		0.30	0.33	2.34	14.2	260	0.84	0.14	12.80	0.77	26.9	5.8	72	1.39	19.4	2.61
18-8546-3		0.28	0.05	2.70	3.2	180	0.90	0.12	12.25	0.10	29.1	4.8	28	1.30	9.2	1.62
18-8546-4		0.30	0.04	2.34	2.7	150	0.69	0.07	13.55	0.02	25.1	4.4	26	1.05	7.9	1.57
18-8546-5		0.28	0.04	1.92	1.8	110	0.62	0.10	14.10	0.04	22.9	3.7	19	0.74	5.2	1.51
18-8546-6		0.26	0.18	2.82	7.1	240	0.79	0.17	11.80	0.39	30.8	6.7	44	1.56	12.3	2.05
18-8546-7		0.28	0.18	3.11	9.3	250	0.86	0.22	10.65	0.38	34.1	7.0	67	1.75	14.0	2.28
18-8546-8		0.28	0.21	3.78	11.0	300	1.14	0.29	8.68	0.35	39.2	9.3	69	2.40	16.4	2.57
18-8546-9		0.26	0.19	2.93	9.1	240	0.88	0.25	11.20	0.29	31.1	6.9	55	1.65	13.7	2.24
18-8546-10		0.28	0.18	2.79	6.8	220	0.76	0.21	12.30	0.36	27.7	7.0	49	1.46	15.9	2.13
18-8546-11		0.28	0.14	2.36	6.2	180	0.64	0.17	13.95	0.29	24.2	4.9	35	1.20	9.6	1.90
18-8546-12		0.26	0.05	2.41	3.0	150	0.72	0.14	12.75	0.04	20.4	3.4	28	1.09	5.5	1.64
18-8546-13		0.28	0.06	2.26	2.7	140	0.68	0.13	13.90	0.08	22.3	3.9	19	0.95	7.0	1.55
18-8546-14		0.28	0.03	2.32	7.0	130	0.73	0.15	12.40	0.06	23.0	4.4	31	1.08	7.8	1.60
18-8546-15		0.28	0.18	4.08	9.2	310	1.14	0.27	7.64	0.37	41.0	10.6	76	2.62	17.3	2.79
18-8546-16		0.30	0.01	0.49	0.4	20	0.11	0.01	0.02	<0.02	15.60	0.9	355	0.31	3.4	0.48



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 3 - B  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10
18-8544-21		1.36	<0.05	0.1	<0.005	0.22	6.9	2.6	0.03	44	1.14	0.01	1.1	6.9	30
18-8544-22		24.6	0.07	4.1	1.780	2.03	17.2	15.8	0.43	541	13.55	1.27	8.5	25.0	360
18-8545-1		2.23	0.05	0.3	0.054	0.36	6.6	7.0	9.99	1020	0.26	0.07	1.2	5.4	180
18-8545-2		1.37	0.05	0.2	0.005	0.22	7.2	2.2	0.03	38	0.91	0.01	1.0	5.9	30
18-8545-3		12.25	0.09	1.7	0.059	3.03	25.9	39.6	4.62	1430	0.36	0.04	6.9	21.2	540
18-8545-4		8.00	0.07	1.0	0.036	1.88	13.8	32.7	7.16	1430	0.27	0.03	4.0	9.9	290
18-8545-5		7.91	0.08	1.1	0.041	1.75	17.5	32.8	7.16	1210	0.16	0.02	3.9	13.4	330
18-8545-6		14.20	0.08	1.9	0.062	2.89	29.8	51.8	1.59	2340	0.90	0.18	7.3	26.4	600
18-8545-7		14.90	0.07	1.7	0.067	3.15	25.9	56.5	3.15	2660	0.73	0.09	7.7	34.5	480
18-8545-8		10.45	0.06	1.7	0.071	2.36	21.5	35.0	5.59	1690	0.41	0.08	5.4	24.1	490
18-8545-9		9.54	0.06	1.3	0.072	2.05	19.1	36.7	6.14	1830	0.30	0.04	4.7	24.4	420
18-8545-10		10.25	0.06	1.3	0.083	2.12	19.6	34.7	5.36	1990	0.44	0.07	4.9	21.6	530
18-8545-11		8.71	0.08	1.1	0.060	1.85	17.0	32.1	6.15	1850	0.37	0.06	4.3	21.2	440
18-8545-12		7.73	0.06	1.2	0.054	1.66	16.1	29.6	7.03	1590	0.30	0.04	4.2	15.6	360
18-8545-13		7.63	0.05	1.1	0.052	1.70	16.0	30.2	7.15	1420	0.22	0.03	4.1	14.9	350
18-8545-14		6.18	0.06	0.8	0.066	1.38	12.1	23.9	7.54	1510	0.35	0.03	2.9	13.5	280
18-8545-15		6.78	0.06	0.9	0.056	1.50	13.7	27.0	7.72	1300	0.24	0.02	3.2	12.6	290
18-8545-16		6.80	0.06	0.9	0.048	1.51	13.3	29.3	7.80	1330	0.29	0.03	3.4	13.7	320
18-8545-17		8.24	0.08	1.1	0.064	1.75	14.9	32.9	7.36	1460	0.30	0.03	3.9	17.0	330
18-8545-18		9.86	0.07	1.3	0.057	2.10	19.7	38.7	6.63	1420	0.28	0.03	4.8	19.3	410
18-8545-19		7.58	0.07	1.1	0.068	1.56	14.8	32.3	8.01	1500	0.32	0.03	4.0	16.7	310
18-8545-20		7.01	0.07	1.1	0.045	1.80	13.7	28.3	7.62	1350	0.21	0.03	3.6	12.5	330
18-8545-21		1.40	0.05	0.2	0.005	0.22	7.2	2.3	0.02	37	1.18	0.01	1.2	6.6	20
18-8545-22		24.8	0.08	4.4	1.840	2.12	17.3	17.2	0.44	566	14.10	1.32	8.9	24.8	370
18-8546-1		2.54	0.05	0.3	0.052	0.39	5.6	10.0	10.85	1060	0.22	0.05	1.0	7.0	160
18-8546-2		5.66	0.06	0.9	0.065	0.92	14.1	16.8	7.82	1770	0.49	0.20	3.7	13.3	420
18-8546-3		7.93	0.08	1.0	0.032	1.92	14.8	36.6	7.60	1360	0.16	0.03	4.4	10.2	280
18-8546-4		6.24	0.06	0.8	0.024	1.70	12.8	30.8	8.00	1200	0.11	0.02	3.3	8.2	230
18-8546-5		4.81	0.07	0.6	0.038	1.36	11.9	22.5	8.69	1350	0.09	0.02	2.4	7.1	180
18-8546-6		7.17	0.08	1.0	0.036	1.74	15.3	31.4	6.73	1650	0.24	0.09	4.1	12.4	310
18-8546-7		7.94	0.07	1.1	0.038	1.89	16.4	34.1	6.61	1850	0.42	0.10	4.6	13.7	350
18-8546-8		9.33	0.10	1.3	0.045	2.35	18.9	34.3	5.64	1880	0.44	0.12	5.6	15.3	400
18-8546-9		7.33	0.08	1.0	0.038	1.76	14.9	31.4	6.99	1790	0.47	0.10	4.3	12.2	310
18-8546-10		6.83	0.06	0.9	0.033	1.77	14.1	31.2	7.10	1930	0.28	0.08	4.0	10.9	310
18-8546-11		5.68	0.07	0.8	0.037	1.59	12.2	26.5	7.80	1790	0.23	0.05	3.1	9.2	250
18-8546-12		6.04	0.06	0.8	0.030	1.84	10.4	27.7	7.88	1570	0.11	0.02	3.1	8.0	230
18-8546-13		5.65	0.06	0.7	0.026	1.63	11.3	27.1	8.10	1210	0.13	0.02	2.9	9.2	200
18-8546-14		6.65	0.08	0.8	0.025	1.60	11.8	28.9	7.61	1340	0.17	0.03	3.3	7.5	220
18-8546-15		10.30	0.08	1.4	0.053	2.39	19.7	41.4	5.20	1830	0.48	0.13	5.8	17.9	480
18-8546-16		1.44	<0.05	0.2	<0.005	0.22	7.3	2.1	0.03	34	0.87	0.01	1.1	5.3	30





ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 3 - C  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U
		ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
		0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005	0.02	0.1
18-8544-21		5.5	<0.002	<0.01	0.23	0.8	<1	0.4	5.8	0.05	<0.05	2.75	0.041	0.03	0.4
18-8544-22		71.0	<0.002	4.43	143.0	5.6	4	5.1	89.3	0.65	0.07	6.33	0.152	1.94	2.5
18-8545-1		12.8	<0.002	0.01	1.01	1.8	1	0.4	32.3	0.08	<0.05	1.39	0.041	0.19	0.3
18-8545-2		5.4	<0.002	<0.01	0.22	0.8	<1	0.3	5.8	0.05	<0.05	2.76	0.040	0.03	0.3
18-8545-3		102.5	<0.002	0.01	1.22	8.2	1	2.0	22.9	0.53	<0.05	8.64	0.218	0.40	1.3
18-8545-4		55.5	<0.002	0.01	1.00	5.1	<1	1.1	26.5	0.30	<0.05	5.01	0.135	0.28	0.9
18-8545-5		59.1	<0.002	0.01	0.92	5.2	<1	1.1	27.0	0.30	0.05	5.46	0.121	0.23	0.8
18-8545-6		110.0	<0.002	0.04	2.28	9.6	<1	1.7	28.7	0.55	<0.05	9.12	0.243	0.50	1.8
18-8545-7		109.5	<0.002	0.03	1.88	9.3	<1	1.9	23.4	0.56	0.05	9.25	0.235	0.53	1.6
18-8545-8		84.6	<0.002	0.03	1.40	7.5	<1	1.4	31.7	0.39	<0.05	6.91	0.175	0.36	1.1
18-8545-9		73.3	<0.002	0.03	1.20	6.3	<1	1.3	26.3	0.36	0.06	6.44	0.155	0.35	0.9
18-8545-10		75.2	<0.002	0.04	1.55	7.3	<1	1.4	29.1	0.35	<0.05	6.56	0.163	0.40	1.0
18-8545-11		65.9	<0.002	0.02	1.35	6.3	<1	1.2	28.8	0.31	<0.05	5.88	0.136	0.48	0.9
18-8545-12		58.7	<0.002	0.01	1.20	5.5	<1	1.0	31.1	0.30	<0.05	5.41	0.131	0.44	0.9
18-8545-13		57.5	<0.002	0.01	1.05	5.3	<1	1.0	29.9	0.32	<0.05	5.39	0.131	0.35	0.8
18-8545-14		46.0	<0.002	0.02	0.95	4.4	1	0.8	31.3	0.20	<0.05	3.85	0.094	0.21	0.6
18-8545-15		50.4	<0.002	0.01	0.86	4.5	<1	0.9	29.1	0.24	<0.05	4.45	0.099	0.21	0.7
18-8545-16		50.4	<0.002	0.01	0.91	4.6	<1	1.0	27.3	0.25	<0.05	4.78	0.107	0.24	0.7
18-8545-17		62.7	<0.002	0.01	1.39	5.3	<1	1.1	28.5	0.30	<0.05	5.45	0.126	0.30	0.8
18-8545-18		76.0	<0.002	0.01	1.38	6.6	<1	1.3	27.7	0.36	0.06	6.73	0.155	0.35	1.0
18-8545-19		57.8	<0.002	<0.01	1.39	5.4	<1	1.0	30.9	0.26	<0.05	4.70	0.113	0.30	0.8
18-8545-20		53.5	<0.002	0.01	1.15	4.5	<1	0.9	23.0	0.30	0.06	5.14	0.124	0.24	0.8
18-8545-21		5.6	<0.002	<0.01	0.25	0.8	<1	0.4	5.8	0.05	<0.05	2.87	0.042	0.03	0.4
18-8545-22		72.9	<0.002	4.60	145.0	5.8	3	5.0	93.1	0.68	0.11	6.42	0.161	2.04	2.7
18-8546-1		14.0	<0.002	0.01	0.64	2.9	<1	0.3	31.6	0.06	0.05	1.09	0.059	0.11	0.2
18-8546-2		36.1	<0.002	0.03	1.14	4.8	<1	0.8	48.9	0.26	<0.05	3.80	0.130	0.42	0.8
18-8546-3		56.8	<0.002	0.01	0.77	5.4	<1	1.1	27.7	0.29	<0.05	4.41	0.123	0.22	0.8
18-8546-4		44.2	<0.002	<0.01	0.51	4.4	<1	0.8	25.5	0.24	<0.05	3.68	0.104	0.17	0.7
18-8546-5		35.1	<0.002	<0.01	0.47	3.5	<1	0.6	28.8	0.17	<0.05	3.10	0.077	0.14	0.6
18-8546-6		48.6	<0.002	0.01	1.05	5.2	<1	0.8	36.9	0.30	0.05	4.64	0.133	0.31	0.9
18-8546-7		54.0	<0.002	0.01	1.03	5.7	<1	1.0	35.0	0.33	0.05	4.97	0.148	0.34	1.1
18-8546-8		71.8	<0.002	0.01	1.32	6.5	<1	1.2	36.7	0.41	0.06	6.60	0.181	0.40	1.3
18-8546-9		48.3	<0.002	0.01	0.96	5.3	<1	1.0	35.0	0.31	<0.05	4.69	0.136	0.30	1.0
18-8546-10		47.5	<0.002	0.02	1.04	4.9	<1	0.9	33.8	0.28	<0.05	4.49	0.130	0.27	0.9
18-8546-11		40.2	<0.002	0.01	0.78	4.1	<1	0.7	32.0	0.24	0.05	3.74	0.107	0.23	0.8
18-8546-12		45.4	<0.002	0.01	0.55	4.1	<1	0.7	23.6	0.23	0.06	3.67	0.099	0.19	0.7
18-8546-13		42.0	<0.002	<0.01	0.56	4.0	<1	0.7	25.2	0.22	<0.05	3.53	0.093	0.19	0.6
18-8546-14		47.6	<0.002	<0.01	0.65	4.9	<1	0.9	26.1	0.23	<0.05	3.41	0.120	0.19	0.7
18-8546-15		78.3	<0.002	0.03	1.23	7.7	<1	1.3	35.1	0.42	0.06	6.62	0.185	0.43	1.3
18-8546-16		5.6	<0.002	<0.01	0.25	0.8	<1	0.3	5.9	0.05	<0.05	2.81	0.041	0.03	0.4





ALS Canada Ltd.  
 2103 Dollarton Hwy  
 North Vancouver BC V7H 0A7  
 Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
 www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
 203 - 1634 HARVEY AVE  
 KELOWNA BC V1Y 6G2

Page: 3 - D  
 Total # Pages: 6 (A - D)  
 Plus Appendix Pages  
 Finalized Date: 12-NOV-2018  
 Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Pb-OG62 Pb % 0.001	Zn-OG62 Zn % 0.001	Au-ICP22 Au ppm 0.001
18-8544-21		0.1	1.3	2	4.7			<0.001
18-8544-22		2.3	9.7	>10000	153.0	1.370	5.38	1.250
18-8545-1		0.2	10.0	140	11.6			0.002
18-8545-2		0.2	1.3	12	4.7			<0.001
18-8545-3		1.2	17.0	60	55.3			<0.001
18-8545-4		0.7	11.0	76	34.0			0.004
18-8545-5		0.6	11.7	34	33.7			<0.001
18-8545-6		1.1	18.1	212	59.6			0.001
18-8545-7		1.2	17.3	197	58.7			0.004
18-8545-8		0.8	16.1	89	45.7			0.008
18-8545-9		0.8	14.3	87	41.0			0.013
18-8545-10		0.9	17.6	166	43.8			0.027
18-8545-11		0.8	15.7	206	37.4			0.008
18-8545-12		0.8	13.8	210	35.7			0.008
18-8545-13		0.7	12.5	124	34.7			0.018
18-8545-14		0.5	11.3	79	26.4			0.006
18-8545-15		0.5	10.8	51	29.0			0.010
18-8545-16		0.5	10.8	63	30.0			0.011
18-8545-17		0.7	12.0	103	35.3			0.035
18-8545-18		0.8	14.1	68	42.9			0.013
18-8545-19		0.7	13.3	72	35.4			0.026
18-8545-20		0.6	10.5	50	33.5			0.028
18-8545-21		0.1	1.4	<2	5.1			<0.001
18-8545-22		2.5	9.7	>10000	161.0	1.355	5.31	1.220
18-8546-1		0.3	9.2	206	9.6			0.025
18-8546-2		0.6	16.5	230	28.5			0.002
18-8546-3		0.6	11.8	55	36.9			0.004
18-8546-4		0.4	11.5	37	25.9			0.002
18-8546-5		0.3	10.9	33	19.9			0.001
18-8546-6		0.7	12.5	170	31.5			0.002
18-8546-7		0.8	13.9	151	35.7			0.002
18-8546-8		0.9	15.7	156	42.6			0.003
18-8546-9		0.7	13.2	140	33.4			0.003
18-8546-10		0.6	12.4	153	30.5			0.003
18-8546-11		0.5	11.3	124	25.2			0.012
18-8546-12		0.5	8.8	32	24.4			0.001
18-8546-13		0.4	9.6	44	23.0			<0.001
18-8546-14		0.5	10.3	35	25.3			<0.001
18-8546-15		0.9	18.1	162	45.4			0.002
18-8546-16		0.1	1.5	2	4.7			<0.001



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 4 - A  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
18-8546-17		0.28	0.25	4.61	11.7	380	1.46	0.36	4.93	0.53	46.9	11.2	97	3.18	18.9	3.24
18-8546-18		0.28	0.17	3.94	7.5	310	1.11	0.28	6.74	0.45	45.6	9.2	89	2.01	9.6	2.68
18-8546-19		0.28	0.11	3.72	6.2	270	1.03	0.18	8.24	0.25	42.3	7.1	66	2.04	10.7	2.42
18-8546-20		0.26	0.11	3.30	7.3	210	1.07	0.25	10.30	0.18	35.1	6.7	62	1.69	28.5	2.30
18-8546-21		0.22	0.01	0.49	<0.2	20	0.12	0.01	0.02	<0.02	14.55	0.8	398	0.29	3.8	0.51
18-8546-22		0.06	67.6	5.82	80.1	140	1.61	3.89	1.98	277	39.1	27.2	36	3.08	3600	3.63
18-8547-1		0.28	0.21	6.21	11.1	560	1.83	0.29	0.22	0.67	69.4	11.2	305	5.66	36.8	3.47
18-8547-2		0.26	0.23	5.52	11.6	500	1.68	0.35	0.91	0.93	55.3	12.1	225	5.54	39.9	3.69
18-8547-3		0.28	0.12	5.55	11.2	510	1.57	0.27	0.32	1.42	66.2	10.9	260	3.96	25.3	3.10
18-8547-4		0.28	0.20	5.80	12.3	500	1.56	0.28	0.50	1.11	71.3	11.9	221	4.25	23.1	4.33
18-8547-5		0.28	0.34	5.89	18.5	560	1.67	0.38	0.53	1.46	71.1	18.3	200	5.93	43.3	4.36
18-8547-6		0.28	0.16	6.09	11.0	580	1.48	0.30	1.09	0.47	83.3	19.1	152	4.38	31.9	4.79
18-8547-7		0.28	0.15	5.45	10.6	550	1.38	0.37	0.20	0.78	62.4	11.6	247	3.81	22.8	3.45
18-8547-8		0.28	0.32	5.61	17.4	520	1.58	0.36	0.22	1.12	61.7	13.5	242	4.09	30.5	3.74
18-8547-9		0.26	0.60	5.43	26.8	560	1.60	0.45	0.53	1.09	57.6	14.3	300	4.70	57.9	4.10
18-8547-10		0.28	0.66	5.41	23.6	560	1.41	0.60	0.53	1.04	60.3	16.8	221	5.36	50.6	4.32
18-8547-11		0.28	0.12	5.83	10.0	560	1.79	0.27	0.32	0.63	67.2	10.9	316	5.05	21.3	3.22
18-8547-12		0.28	0.20	5.67	9.8	560	1.69	0.40	0.32	0.95	67.2	11.7	250	5.07	24.9	3.47
18-8547-13		0.28	0.01	0.47	0.4	20	0.16	0.02	0.01	<0.02	14.45	0.9	352	0.29	4.2	0.44
18-8547-14		0.28	0.37	5.78	25.9	520	1.77	0.61	0.33	1.52	66.9	15.2	249	5.14	33.6	3.88
18-8547-15		0.24	0.20	4.60	16.2	360	1.41	0.33	6.70	1.04	50.8	13.8	79	3.97	28.6	2.98
18-8547-16		0.26	0.25	4.20	27.2	340	1.22	0.36	7.45	1.17	47.0	13.6	91	3.68	26.4	3.31
18-8547-17		0.30	0.33	5.86	124.0	570	1.51	0.47	0.23	1.89	57.5	25.3	224	4.08	50.3	4.57
18-8547-18		0.28	1.37	6.31	1470	510	1.40	1.30	0.24	15.70	45.4	39.3	192	4.60	142.0	8.24
18-8547-19		0.26	2.98	5.27	362	390	1.45	1.63	0.59	41.0	33.7	22.2	241	3.61	149.5	10.25
18-8547-20		0.30	3.05	5.60	108.0	440	1.35	0.90	1.36	15.45	37.8	21.4	207	3.92	100.5	6.48
18-8547-21		0.22	0.02	0.49	0.6	20	0.11	0.01	0.01	0.03	15.10	0.8	415	0.30	4.2	0.51
18-8547-22		0.06	66.6	6.08	78.7	110	1.68	4.07	1.93	274	48.4	27.3	36	3.14	3540	3.63
18-8548-1		0.30	0.18	3.39	9.3	300	0.90	0.20	8.72	0.84	38.9	6.5	86	1.46	24.7	2.85
18-8548-2		0.26	0.39	4.04	18.0	410	1.35	0.29	6.30	1.12	46.8	8.6	102	2.17	52.8	3.70
18-8548-3		0.28	0.26	0.90	13.8	70	0.45	0.07	17.50	0.58	12.90	2.1	33	0.51	7.0	1.46
18-8548-4		0.30	0.19	0.49	3.5	30	0.32	0.05	18.95	0.53	7.68	1.3	10	0.23	4.8	1.04
18-8548-5		0.28	0.24	0.80	6.3	50	0.37	0.07	18.10	0.53	10.25	1.9	24	0.43	7.0	1.37
18-8548-6		0.28	0.51	1.29	17.9	100	0.64	0.15	16.10	1.22	15.85	3.0	40	0.73	11.5	2.07
18-8548-7		0.28	0.46	0.96	8.6	70	0.46	0.09	17.25	0.79	12.35	2.4	35	0.52	10.9	1.59
18-8548-8		0.28	0.17	1.09	17.2	100	0.58	0.08	17.90	0.39	15.50	2.7	32	0.64	15.3	1.79
18-8548-9		0.28	0.02	0.48	0.5	20	0.12	0.01	0.03	0.02	14.45	0.7	393	0.29	3.2	0.48
18-8548-10		0.28	0.12	0.96	15.0	70	0.36	0.06	18.35	0.31	12.45	2.3	24	0.46	12.0	1.45
18-8548-11		0.28	0.13	1.04	10.8	80	0.44	0.05	17.85	0.17	11.95	3.0	27	0.53	12.7	1.58
18-8548-12		0.28	0.07	0.72	16.0	50	0.39	0.04	18.95	0.11	9.36	2.1	17	0.37	6.4	1.27



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 4 - B  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10
18-8546-17		11.95	0.08	1.6	0.063	2.62	22.4	43.8	3.75	2260	0.67	0.17	6.5	21.3	670
18-8546-18		10.10	0.07	1.4	0.046	2.30	21.6	40.2	4.87	2050	0.41	0.09	5.8	16.6	500
18-8546-19		9.48	0.07	1.2	0.041	2.33	19.6	36.9	5.48	1690	0.39	0.06	5.4	14.5	470
18-8546-20		8.34	0.06	1.1	0.047	2.13	16.4	30.3	6.39	1510	0.30	0.05	4.8	14.5	360
18-8546-21		1.34	0.05	0.1	0.005	0.22	6.9	2.1	0.02	38	1.15	0.01	1.1	6.4	20
18-8546-22		24.1	0.10	4.2	1.810	2.09	17.6	16.4	0.45	559	13.95	1.31	8.8	23.1	370
18-8547-1		15.35	0.08	2.2	0.062	3.29	34.1	29.4	1.21	1640	1.24	0.16	8.7	26.0	420
18-8547-2		13.20	0.09	1.8	0.072	2.60	26.4	21.4	1.19	1670	0.96	0.27	8.7	21.2	700
18-8547-3		13.65	0.07	2.0	0.066	3.03	31.8	22.2	1.00	2290	0.99	0.19	8.9	19.3	400
18-8547-4		14.35	0.09	1.9	0.093	2.95	35.4	23.4	0.92	3460	0.97	0.15	10.8	21.7	810
18-8547-5		14.50	0.09	2.0	0.084	2.84	35.0	26.6	1.26	2910	1.06	0.35	11.4	27.7	710
18-8547-6		15.20	0.11	2.2	0.068	2.42	41.8	25.6	1.46	2280	0.90	0.70	19.8	22.2	1560
18-8547-7		13.35	0.09	1.9	0.104	3.12	30.6	22.3	0.78	2990	1.12	0.14	8.2	23.6	340
18-8547-8		13.75	0.07	1.9	0.076	3.01	30.4	24.3	0.91	2870	1.18	0.14	8.4	24.9	430
18-8547-9		13.10	0.07	1.9	0.097	2.77	28.1	24.6	0.91	3000	1.36	0.23	7.3	27.8	490
18-8547-10		13.25	0.10	1.9	0.120	2.53	29.9	26.3	0.96	3070	1.27	0.29	7.6	25.9	600
18-8547-11		14.25	0.08	2.0	0.067	3.26	32.2	25.5	1.04	1870	1.19	0.18	8.4	29.0	430
18-8547-12		14.00	0.09	1.9	0.074	3.01	32.5	27.3	1.04	2000	1.22	0.22	8.8	21.4	530
18-8547-13		1.24	<0.05	0.1	<0.005	0.21	6.8	2.3	0.02	34	0.98	0.01	1.0	8.3	30
18-8547-14		13.90	0.10	2.0	0.081	3.09	32.4	29.4	1.01	2340	1.21	0.18	8.0	26.9	500
18-8547-15		11.85	0.06	1.5	0.063	2.72	23.8	28.0	4.31	1530	0.89	0.07	5.6	24.3	310
18-8547-16		10.35	0.07	1.4	0.073	2.38	22.6	23.1	4.65	1860	0.98	0.09	5.2	23.8	350
18-8547-17		14.80	0.07	1.7	0.096	3.03	26.2	28.0	1.09	3230	1.23	0.12	5.8	37.5	440
18-8547-18		16.50	0.09	1.2	0.156	3.05	20.1	25.3	1.10	6480	0.98	0.08	4.2	45.7	630
18-8547-19		15.55	0.08	0.7	0.230	2.65	15.9	17.1	0.79	9400	1.27	0.04	2.6	33.6	460
18-8547-20		14.45	0.06	0.9	0.192	2.86	16.5	23.9	1.14	4880	1.11	0.05	3.2	27.5	500
18-8547-21		1.38	<0.05	0.2	<0.005	0.22	7.0	2.4	0.02	45	1.13	0.01	1.1	7.3	30
18-8547-22		24.2	0.06	4.1	1.810	2.08	21.7	15.7	0.46	557	13.75	1.28	8.6	24.9	350
18-8548-1		8.32	0.07	1.1	0.068	2.12	18.0	31.2	5.34	2650	0.48	0.08	4.3	14.4	400
18-8548-2		9.72	0.05	1.4	0.081	2.00	22.7	33.1	4.49	3020	0.66	0.21	5.6	20.4	550
18-8548-3		2.33	<0.05	0.4	0.048	0.44	6.8	8.6	10.20	1130	0.22	0.06	1.2	5.8	150
18-8548-4		1.37	<0.05	0.2	0.042	0.25	4.1	6.0	11.00	868	0.09	0.02	0.6	3.0	80
18-8548-5		2.03	0.05	0.3	0.059	0.36	5.4	8.0	10.40	1120	0.17	0.05	1.0	4.8	150
18-8548-6		3.04	0.05	0.6	0.079	0.53	8.5	9.9	9.39	1620	0.39	0.09	1.6	7.3	280
18-8548-7		2.52	0.07	0.4	0.068	0.40	6.6	8.9	10.00	1260	0.28	0.06	1.2	6.1	200
18-8548-8		2.66	0.07	0.4	0.072	0.45	8.3	9.5	10.35	1390	0.25	0.08	1.4	7.2	230
18-8548-9		1.23	<0.05	0.2	<0.005	0.22	6.7	2.2	0.03	42	1.44	0.01	1.1	5.4	30
18-8548-10		2.48	<0.05	0.3	0.059	0.44	6.6	9.1	10.55	1140	0.20	0.05	1.1	6.3	170
18-8548-11		2.76	<0.05	0.3	0.066	0.39	6.4	9.8	10.45	1110	0.20	0.06	1.2	8.3	200
18-8548-12		1.81	<0.05	0.2	0.045	0.28	5.1	7.3	11.15	937	0.15	0.04	0.8	6.1	130



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 4 - C  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U
		ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
		0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005	0.02	0.1
18-8546-17		89.7	<0.002	0.04	1.52	8.8	<1	1.5	39.2	0.49	<0.05	7.66	0.211	0.59	1.6
18-8546-18		75.6	<0.002	0.02	1.15	7.0	<1	1.3	27.1	0.45	<0.05	6.64	0.184	0.46	1.2
18-8546-19		75.6	<0.002	0.02	1.04	6.7	1	1.3	26.7	0.41	<0.05	6.45	0.178	0.48	1.1
18-8546-20		69.1	<0.002	0.01	0.97	6.3	<1	1.1	28.4	0.34	0.05	5.33	0.155	0.30	0.9
18-8546-21		5.6	<0.002	<0.01	0.23	0.9	<1	0.4	5.7	0.05	<0.05	2.59	0.043	0.04	0.3
18-8546-22		73.0	<0.002	4.56	144.0	5.6	2	5.3	91.1	0.67	0.06	6.34	0.160	2.00	2.6
18-8547-1		152.5	<0.002	0.02	2.17	9.4	<1	2.0	25.2	0.62	<0.05	11.90	0.268	0.59	1.8
18-8547-2		135.0	<0.002	0.05	1.95	9.4	<1	1.6	37.6	0.59	<0.05	9.70	0.292	0.46	1.7
18-8547-3		134.5	<0.002	0.02	1.91	8.3	<1	1.8	23.3	0.62	0.06	10.00	0.272	0.49	1.5
18-8547-4		136.5	<0.002	0.03	2.18	9.9	<1	1.8	31.1	0.68	<0.05	10.35	0.351	0.46	1.8
18-8547-5		140.0	<0.002	0.03	2.64	10.7	<1	1.7	44.8	0.71	<0.05	10.70	0.397	0.63	2.0
18-8547-6		109.0	<0.002	0.03	2.19	12.2	<1	1.7	95.7	1.12	<0.05	9.63	0.650	0.48	1.7
18-8547-7		137.0	<0.002	0.01	2.19	8.0	<1	1.7	22.9	0.55	0.05	9.68	0.248	0.55	1.6
18-8547-8		135.5	<0.002	0.02	2.42	8.6	<1	1.8	22.5	0.58	<0.05	9.86	0.267	0.55	1.7
18-8547-9		129.0	<0.002	0.03	3.26	9.5	1	1.7	35.3	0.51	0.06	9.77	0.240	0.52	1.7
18-8547-10		126.0	<0.002	0.04	2.91	9.9	<1	1.6	44.5	0.51	0.05	9.91	0.253	0.57	1.8
18-8547-11		142.0	<0.002	0.02	2.08	8.7	<1	1.9	23.7	0.57	<0.05	10.70	0.265	0.58	1.4
18-8547-12		136.5	0.002	0.02	2.37	9.0	<1	1.7	27.4	0.56	<0.05	10.85	0.283	0.52	1.5
18-8547-13		5.4	<0.002	<0.01	0.24	0.8	<1	0.4	5.6	<0.05	<0.05	2.48	0.039	0.03	0.3
18-8547-14		132.5	<0.002	0.03	3.10	9.2	1	1.8	25.5	0.54	<0.05	10.90	0.267	0.59	1.6
18-8547-15		105.5	<0.002	0.04	2.10	8.1	1	1.5	22.5	0.40	<0.05	8.00	0.197	0.45	1.4
18-8547-16		95.8	<0.002	0.03	2.60	7.6	1	1.3	24.2	0.38	<0.05	7.51	0.176	0.42	1.6
18-8547-17		124.0	<0.002	0.02	3.64	12.8	<1	1.7	19.3	0.39	<0.05	9.36	0.265	0.57	1.4
18-8547-18		124.0	<0.002	0.02	7.44	25.4	1	1.8	22.0	0.27	<0.05	5.65	0.320	0.64	1.1
18-8547-19		112.5	<0.002	0.09	19.80	26.1	1	1.7	48.7	0.14	<0.05	4.01	0.196	0.68	1.4
18-8547-20		119.0	<0.002	0.05	11.35	21.4	1	1.9	118.5	0.20	0.06	5.01	0.275	0.68	1.2
18-8547-21		5.6	<0.002	<0.01	0.28	0.8	<1	0.4	5.9	<0.05	<0.05	2.83	0.040	0.04	0.4
18-8547-22		79.4	<0.002	4.55	142.0	5.7	3	4.9	91.8	0.65	0.05	7.35	0.156	1.88	2.6
18-8548-1		61.0	<0.002	0.04	1.24	5.6	1	1.0	30.0	0.32	<0.05	5.19	0.143	0.34	0.9
18-8548-2		66.5	<0.002	0.05	1.72	7.2	1	1.3	43.8	0.39	<0.05	6.49	0.197	0.62	1.2
18-8548-3		15.1	<0.002	0.01	0.88	1.9	<1	0.3	33.8	0.09	<0.05	1.54	0.044	0.21	0.3
18-8548-4		8.3	<0.002	<0.01	0.46	1.2	1	0.2	30.3	<0.05	<0.05	0.74	0.024	0.09	0.1
18-8548-5		12.3	<0.002	0.01	0.52	1.9	<1	0.3	32.0	0.06	<0.05	1.20	0.042	0.13	0.2
18-8548-6		17.9	<0.002	0.02	0.96	2.6	1	0.5	36.2	0.12	<0.05	2.22	0.064	0.24	0.4
18-8548-7		14.0	<0.002	0.01	0.76	2.2	<1	0.3	34.2	0.08	<0.05	1.51	0.049	0.21	0.3
18-8548-8		15.9	<0.002	0.01	0.75	2.4	1	0.4	35.7	0.10	<0.05	1.78	0.055	0.32	0.4
18-8548-9		5.4	<0.002	<0.01	0.25	0.7	<1	0.4	5.9	<0.05	<0.05	2.59	0.040	0.03	0.3
18-8548-10		14.2	<0.002	<0.01	0.62	2.5	<1	0.3	30.4	0.08	<0.05	1.35	0.058	0.23	0.3
18-8548-11		13.9	<0.002	0.01	0.84	3.3	1	0.3	32.8	0.07	<0.05	1.22	0.072	0.38	0.3
18-8548-12		9.6	<0.002	0.01	1.48	2.0	<1	0.2	29.8	0.05	<0.05	0.98	0.045	0.53	0.2



ALS Canada Ltd.  
 2103 Dollarton Hwy  
 North Vancouver BC V7H 0A7  
 Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
 www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
 203 - 1634 HARVEY AVE  
 KELOWNA BC V1Y 6G2

Page: 4 - D  
 Total # Pages: 6 (A - D)  
 Plus Appendix Pages  
 Finalized Date: 12-NOV-2018  
 Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Pb-OG62 Pb % 0.001	Zn-OG62 Zn % 0.001	Au-ICP22 Au ppm 0.001
18-8546-17		1.2	21.7	223	50.6			0.003
18-8546-18		1.0	18.3	182	44.3			0.001
18-8546-19		0.9	17.6	123	40.8			<0.001
18-8546-20		0.7	13.8	73	36.7			0.002
18-8546-21		0.1	1.5	<2	5.9			<0.001
18-8546-22		2.4	9.7	>10000	158.5	1.310	5.09	1.250
18-8547-1		1.1	10.6	266	76.0			0.001
18-8547-2		1.0	11.4	394	61.4			<0.001
18-8547-3		1.1	9.5	405	65.7			0.001
18-8547-4		1.6	15.1	390	66.7			0.001
18-8547-5		1.1	15.9	574	71.5			<0.001
18-8547-6		1.1	18.8	276	81.8			0.001
18-8547-7		1.0	10.4	288	64.8			<0.001
18-8547-8		1.1	11.7	394	65.7			<0.001
18-8547-9		1.0	15.3	512	63.8			0.001
18-8547-10		1.0	16.1	551	69.8			0.001
18-8547-11		1.0	9.2	253	66.8			<0.001
18-8547-12		1.0	11.2	333	68.4			<0.001
18-8547-13		0.1	1.3	3	4.0			<0.001
18-8547-14		1.0	11.6	675	72.4			<0.001
18-8547-15		0.8	9.8	315	52.0			<0.001
18-8547-16		0.8	10.4	390	46.9			<0.001
18-8547-17		1.0	11.9	1110	58.9			<0.001
18-8547-18		2.0	11.0	5520	38.0			0.003
18-8547-19		2.6	9.0	8270	24.4			0.001
18-8547-20		2.5	8.6	3410	30.3			<0.001
18-8547-21		0.1	1.5	8	5.0			<0.001
18-8547-22		2.4	11.2	>10000	157.5	1.350	5.23	1.250
18-8548-1		0.7	17.1	326	36.2			0.002
18-8548-2		0.9	22.7	398	46.8			0.002
18-8548-3		0.2	9.9	182	11.6			0.001
18-8548-4		0.1	8.0	110	6.0			0.001
18-8548-5		0.3	9.8	153	9.9			0.001
18-8548-6		0.4	13.5	378	18.5			<0.001
18-8548-7		0.3	11.2	238	12.9			0.002
18-8548-8		0.2	12.7	151	14.8			0.001
18-8548-9		0.1	1.4	4	4.5			<0.001
18-8548-10		0.2	10.5	107	11.1			<0.001
18-8548-11		0.3	11.3	90	10.9			<0.001
18-8548-12		0.2	9.5	67	11.2			<0.001



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 5 - A  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

# CERTIFICATE OF ANALYSIS VA18266880

Sample Description	Method Analyte Units LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
18-8548-13		0.30	0.21	0.81	6.8	70	0.45	0.05	18.65	0.34	11.50	1.8	18	0.49	7.1	1.29
18-8548-14		0.28	0.15	0.62	4.9	50	0.33	0.04	19.05	0.23	9.83	1.6	14	0.37	6.0	1.16
18-8548-15		0.28	0.12	0.50	3.2	40	0.29	0.03	19.95	0.19	8.56	1.2	11	0.29	4.3	1.10
18-8548-16		0.28	0.10	0.48	2.8	30	0.32	0.03	19.60	0.14	8.26	1.1	8	0.26	5.0	0.96
18-8548-17		0.28	0.11	1.30	6.3	80	0.52	0.06	17.45	0.21	17.15	2.5	24	0.69	6.9	1.57
18-8548-18		0.28	0.12	2.73	6.6	140	0.72	0.40	11.50	0.11	25.0	4.5	48	1.27	7.7	1.95
18-8548-19		0.26	0.09	3.33	8.0	180	0.99	0.27	10.35	0.13	34.6	6.7	43	1.64	22.7	2.26
18-8548-20		0.28	0.06	3.61	7.8	170	1.05	0.18	10.85	0.08	42.6	6.4	32	1.63	9.7	2.10
18-8548-21		0.22	0.01	0.52	0.6	20	0.12	0.01	0.02	<0.02	15.95	0.9	442	0.31	4.0	0.53
18-8548-22		0.06	66.9	6.15	79.7	110	1.86	4.25	1.98	273	49.3	27.6	38	3.27	3580	3.63
18-8549-1		0.32	0.30	5.65	36.3	590	1.63	0.48	0.24	1.87	69.0	24.3	205	4.35	30.7	3.57
18-8549-2		0.28	2.56	6.34	12.9	460	2.16	1.53	0.08	0.50	66.5	15.0	126	4.53	1220	3.63
18-8549-3		0.34	0.02	0.47	0.4	20	0.15	0.02	0.01	0.02	15.20	0.9	401	0.31	6.1	0.46
18-8549-4		0.26	0.31	6.62	35.5	450	2.60	0.60	0.34	0.79	72.8	18.4	129	6.89	27.9	3.13
18-8549-5		0.26	0.59	6.30	13.6	510	2.51	0.94	0.21	0.27	66.5	33.5	134	7.84	83.8	5.21
18-8549-6		0.26	0.87	6.61	28.8	450	2.51	1.26	0.52	0.51	72.0	53.9	125	7.08	123.5	6.37
18-8549-7		0.30	0.60	6.45	3.7	530	2.51	0.91	0.12	0.34	69.3	44.9	143	7.95	126.5	5.96
18-8549-8		0.28	0.21	6.42	12.2	620	2.41	0.33	0.08	0.29	69.1	26.3	162	6.02	49.4	3.82
18-8549-9		0.30	0.38	6.71	11.3	560	2.74	0.73	0.07	0.38	70.6	39.5	134	6.93	75.0	4.88
18-8549-10		0.28	0.54	6.08	21.1	550	2.42	0.80	0.25	0.98	66.6	45.1	163	5.70	99.3	5.08
18-8549-11		0.30	0.47	6.36	17.3	570	2.32	0.56	0.67	1.18	69.4	32.4	139	5.56	60.7	4.30
18-8549-12		0.28	0.40	6.64	36.4	540	2.72	0.59	0.07	0.47	70.3	31.3	169	5.32	60.0	4.39
18-8549-13		0.28	0.33	6.74	37.9	530	2.62	0.38	0.07	0.36	71.4	25.3	141	5.53	42.7	4.12
18-8549-14		0.28	0.26	7.01	41.9	520	2.37	0.85	0.11	0.60	68.3	21.7	145	4.78	67.3	4.49
18-8549-15		0.30	1.15	6.45	205	430	1.90	1.49	0.20	2.53	58.7	28.2	170	4.78	121.0	6.42
18-8549-16		0.26	0.40	6.57	13.5	540	2.42	0.36	0.12	0.80	70.1	16.9	142	7.85	46.5	3.80
18-8549-17		0.28	0.33	6.50	7.6	540	2.45	0.58	0.11	0.39	69.3	23.1	129	8.02	65.7	4.18
18-8549-18		0.28	0.07	4.70	6.8	320	1.55	0.26	7.28	0.09	55.6	9.0	53	2.51	10.1	2.41
18-8549-19		0.28	0.12	3.73	8.1	270	1.29	0.27	10.85	0.15	40.5	7.5	37	2.25	12.0	1.97
18-8549-20		0.28	0.22	4.18	14.0	270	1.36	0.52	9.76	0.18	45.6	9.9	68	2.97	20.8	2.36
18-8549-21		0.22	0.01	0.50	0.3	20	0.14	0.01	0.01	<0.02	15.45	0.8	423	0.32	3.9	0.51
18-8549-22		0.06	67.8	5.77	81.8	130	1.65	3.91	1.94	274	42.0	26.2	36	3.15	3580	3.63
18-8550-1		0.28	0.41	3.17	9.2	240	0.84	0.21	10.85	0.77	36.5	6.1	66	1.72	13.9	2.33
18-8550-2		0.32	0.37	2.63	8.4	190	0.76	0.18	11.55	0.69	27.7	5.6	57	1.40	11.1	2.02
18-8550-3		0.30	0.27	1.64	6.0	90	0.56	0.12	14.70	0.48	17.05	3.4	61	0.70	6.2	1.79
18-8550-4		0.28	0.08	2.17	3.6	120	0.67	0.13	12.60	0.20	22.9	3.3	44	0.92	7.5	1.78
18-8550-5		0.28	0.16	1.97	3.9	130	0.55	0.09	13.20	0.30	24.2	3.6	29	1.06	3.1	1.61
18-8550-6		0.30	0.32	2.75	4.0	180	0.83	0.12	11.25	0.24	26.6	4.0	62	1.31	6.6	1.78
18-8550-7		0.30	0.18	2.82	6.0	200	0.93	0.14	11.15	0.51	28.9	5.2	84	1.54	8.7	2.01
18-8550-8		0.30	0.18	2.62	6.2	190	0.93	0.10	11.80	1.73	27.6	4.9	47	1.32	7.2	1.87



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 5 - B  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
		0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10
18-8548-13		2.10	0.06	0.3	0.043	0.34	6.3	8.1	10.80	1040	0.20	0.07	1.1	4.6	160
18-8548-14		1.63	0.06	0.3	0.037	0.27	5.3	6.7	11.00	999	0.16	0.05	0.8	3.9	120
18-8548-15		1.40	0.06	0.2	0.048	0.24	4.6	6.2	11.50	964	0.10	0.04	0.6	3.1	90
18-8548-16		1.31	0.05	0.2	0.040	0.24	4.4	6.2	11.35	834	0.08	0.03	0.6	2.6	80
18-8548-17		3.37	0.05	0.6	0.062	0.61	8.9	13.2	10.15	1240	0.22	0.05	1.6	6.9	200
18-8548-18		6.71	0.06	0.9	0.042	1.75	12.0	26.9	7.19	1420	0.26	0.03	3.3	11.6	260
18-8548-19		8.20	0.06	1.1	0.049	2.11	15.7	33.1	6.63	1480	0.26	0.03	4.3	27.3	340
18-8548-20		9.31	0.08	1.3	0.048	2.25	20.0	36.1	6.97	1260	0.18	0.03	4.9	18.2	420
18-8548-21		1.35	<0.05	0.2	<0.005	0.24	7.4	2.2	0.03	42	1.22	0.01	1.2	7.4	30
18-8548-22		24.4	0.11	4.1	1.785	2.10	22.4	16.7	0.47	553	13.90	1.31	8.8	25.5	360
18-8549-1		13.00	0.07	2.0	0.051	3.11	32.2	26.1	1.01	2550	1.45	0.11	6.2	41.2	360
18-8549-2		15.85	0.08	2.2	0.097	3.23	32.1	56.3	1.73	649	1.01	0.05	6.8	32.4	290
18-8549-3		1.47	<0.05	0.2	<0.005	0.21	7.1	2.1	0.02	35	1.41	0.01	1.1	10.2	20
18-8549-4		18.50	0.09	2.3	0.054	3.99	35.8	58.8	1.49	704	1.43	0.05	8.0	38.9	390
18-8549-5		17.55	0.10	2.3	0.056	3.94	33.4	60.9	2.04	721	2.26	0.05	6.1	58.3	420
18-8549-6		17.85	0.11	2.3	0.065	3.66	35.5	60.3	1.63	1730	3.11	0.09	5.8	76.7	470
18-8549-7		17.50	0.11	2.1	0.056	3.89	34.1	63.3	1.72	445	2.34	0.18	6.2	59.6	380
18-8549-8		16.90	0.12	2.2	0.054	4.11	34.0	54.2	1.22	473	1.99	0.13	7.7	39.9	330
18-8549-9		18.70	0.12	2.3	0.056	3.98	35.1	64.8	1.37	457	2.39	0.10	7.1	51.7	360
18-8549-10		16.60	0.09	2.2	0.055	3.65	32.9	58.8	1.46	593	2.02	0.20	6.5	57.3	410
18-8549-11		17.50	0.11	2.3	0.062	3.79	35.3	63.4	1.69	518	1.61	0.20	7.1	45.9	410
18-8549-12		17.85	0.11	2.4	0.056	3.77	34.6	53.5	1.21	776	1.77	0.11	7.5	42.4	340
18-8549-13		18.45	0.11	2.3	0.045	3.81	34.3	51.3	1.11	807	1.38	0.08	8.0	40.6	340
18-8549-14		19.25	0.09	2.2	0.056	3.79	33.6	53.3	1.64	949	1.04	0.08	7.4	36.6	420
18-8549-15		17.65	0.09	1.6	0.111	3.33	29.1	48.1	1.53	2600	1.48	0.12	4.9	45.3	450
18-8549-16		18.10	0.09	2.6	0.059	3.90	35.0	69.5	1.95	652	1.26	0.12	8.2	39.6	410
18-8549-17		18.00	0.09	2.3	0.051	4.00	34.9	71.5	1.74	470	1.72	0.06	7.5	44.3	380
18-8549-18		13.15	0.12	1.8	0.053	3.42	25.6	45.2	4.98	1170	0.28	0.05	7.9	22.9	550
18-8549-19		9.50	0.08	1.5	0.045	2.82	18.8	32.5	6.73	1270	0.27	0.08	5.4	17.2	360
18-8549-20		11.30	0.09	1.8	0.059	2.87	21.0	36.9	6.13	1570	0.51	0.07	6.5	22.7	440
18-8549-21		1.53	0.05	0.2	<0.005	0.22	7.3	2.3	0.02	39	1.33	0.01	1.2	7.4	20
18-8549-22		26.1	0.08	4.4	1.735	2.07	18.0	14.9	0.44	556	14.95	1.30	9.3	25.2	360
18-8550-1		8.26	0.08	1.1	0.041	1.78	17.2	30.0	6.59	1810	0.41	0.08	4.6	14.4	340
18-8550-2		7.19	0.07	0.9	0.042	1.46	13.8	25.8	7.27	1600	0.32	0.07	4.0	12.6	280
18-8550-3		4.39	0.05	0.6	0.031	0.84	8.5	18.0	8.55	1570	0.29	0.04	2.1	7.9	200
18-8550-4		5.92	0.05	0.7	0.028	1.22	11.6	24.0	7.83	1350	0.17	0.04	2.9	8.5	230
18-8550-5		5.99	0.07	0.7	0.036	1.15	11.8	22.6	8.33	1120	0.23	0.03	3.3	9.1	190
18-8550-6		7.72	0.07	0.9	0.032	1.77	12.9	26.2	6.97	1380	0.29	0.04	4.1	10.2	270
18-8550-7		7.89	0.08	1.1	0.042	1.70	14.2	26.3	6.95	1560	0.39	0.07	4.5	12.5	360
18-8550-8		7.16	0.07	1.0	0.029	1.49	13.7	25.5	7.55	1510	0.22	0.04	3.9	11.4	280





ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 5 - C  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl	U
		ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
		0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.01	0.005	0.02	0.1
18-8548-13		11.9	<0.002	0.01	0.69	1.7	<1	0.3	37.0	0.08	<0.05	1.37	0.041	0.16	0.3
18-8548-14		9.5	<0.002	0.01	0.54	1.4	1	0.3	34.6	0.06	<0.05	1.12	0.030	0.13	0.2
18-8548-15		7.9	<0.002	<0.01	0.49	1.1	1	0.2	33.2	0.05	<0.05	0.85	0.022	0.08	0.2
18-8548-16		8.0	<0.002	<0.01	0.44	1.1	1	0.2	30.6	<0.05	<0.05	0.83	0.021	0.06	0.1
18-8548-17		21.0	<0.002	<0.01	0.67	2.4	1	0.5	33.1	0.12	<0.05	2.41	0.054	0.21	0.4
18-8548-18		52.3	<0.002	<0.01	0.83	5.2	1	0.9	27.0	0.24	<0.05	4.18	0.131	0.24	0.7
18-8548-19		65.0	<0.002	0.01	1.00	6.1	<1	1.1	27.3	0.30	<0.05	5.43	0.158	0.32	0.9
18-8548-20		71.4	<0.002	<0.01	1.01	6.1	<1	1.4	27.5	0.39	<0.05	6.65	0.157	0.28	0.9
18-8548-21		5.7	<0.002	<0.01	0.24	0.8	1	0.4	6.1	0.05	<0.05	2.83	0.044	0.03	0.4
18-8548-22		80.6	<0.002	4.52	144.0	5.7	3	4.9	94.4	0.64	0.07	7.59	0.157	2.14	2.8
18-8549-1		127.0	<0.002	0.02	3.62	8.1	<1	1.6	21.4	0.43	0.10	11.05	0.222	0.61	1.7
18-8549-2		134.5	<0.002	0.05	4.17	9.8	1	1.9	11.5	0.49	0.12	10.80	0.233	0.61	2.0
18-8549-3		5.3	<0.002	<0.01	0.45	0.8	<1	0.4	5.5	0.05	<0.05	2.77	0.039	0.04	0.3
18-8549-4		171.5	<0.002	0.03	4.00	10.0	1	2.1	15.3	0.58	0.08	11.10	0.249	0.76	2.3
18-8549-5		153.5	<0.002	0.08	4.47	10.1	1	2.1	17.3	0.42	0.25	11.05	0.213	0.88	2.8
18-8549-6		155.0	<0.002	0.17	6.15	10.6	1	2.0	19.8	0.40	0.19	11.70	0.211	0.91	3.8
18-8549-7		156.0	<0.002	0.16	5.58	10.3	2	2.0	21.8	0.43	0.14	11.70	0.225	0.92	2.4
18-8549-8		156.5	<0.002	0.07	2.59	9.4	1	2.0	18.2	0.57	0.10	11.60	0.255	0.82	1.9
18-8549-9		162.0	<0.002	0.07	3.93	10.6	1	2.1	17.1	0.48	0.09	11.60	0.235	0.83	2.8
18-8549-10		140.0	<0.002	0.09	4.36	9.5	1	1.9	22.3	0.46	0.10	11.45	0.222	0.79	2.2
18-8549-11		149.5	<0.002	0.10	3.91	9.7	<1	2.0	20.0	0.50	0.07	11.90	0.237	0.73	2.2
18-8549-12		154.5	<0.002	0.05	3.83	10.8	<1	2.1	15.0	0.53	<0.05	11.25	0.257	0.70	1.9
18-8549-13		159.0	<0.002	0.05	3.17	10.8	1	2.1	13.4	0.58	<0.05	11.50	0.264	0.72	1.9
18-8549-14		146.5	<0.002	0.02	2.73	14.1	1	2.0	14.6	0.55	<0.05	10.75	0.310	0.68	1.7
18-8549-15		125.5	<0.002	0.04	4.61	16.5	1	1.6	17.3	0.34	0.05	8.46	0.271	0.64	1.9
18-8549-16		147.5	<0.002	0.05	2.94	10.3	1	2.2	18.3	0.61	<0.05	11.50	0.261	0.79	2.1
18-8549-17		154.5	<0.002	0.09	2.51	10.3	<1	2.0	18.4	0.56	0.09	11.55	0.245	0.84	2.2
18-8549-18		109.5	<0.002	0.01	1.27	7.5	1	1.7	23.2	0.57	0.08	8.58	0.220	0.49	1.4
18-8549-19		84.4	<0.002	0.01	1.23	5.3	<1	1.7	32.1	0.57	<0.05	7.93	0.147	0.38	1.1
18-8549-20		93.3	<0.002	0.01	1.63	6.1	<1	1.9	31.5	0.59	<0.05	8.85	0.175	0.46	1.3
18-8549-21		5.6	<0.002	<0.01	0.28	0.8	<1	0.5	5.9	0.05	<0.05	2.72	0.043	0.04	0.4
18-8549-22		73.8	<0.002	4.55	149.0	5.6	4	5.5	93.7	0.70	<0.05	6.42	0.158	2.13	2.6
18-8550-1		51.8	<0.002	0.02	1.57	5.1	<1	1.1	31.1	0.33	<0.05	5.03	0.141	0.39	1.0
18-8550-2		43.0	<0.002	0.01	1.30	4.4	1	0.9	30.4	0.30	<0.05	4.33	0.122	0.33	0.8
18-8550-3		23.3	<0.002	0.02	0.87	2.8	<1	0.5	28.3	0.15	<0.05	2.38	0.068	0.20	0.5
18-8550-4		34.7	<0.002	0.01	0.70	3.7	<1	0.7	28.0	0.22	<0.05	3.14	0.090	0.18	0.6
18-8550-5		41.1	<0.002	<0.01	0.75	3.4	1	0.7	28.3	0.21	<0.05	3.38	0.087	0.20	0.6
18-8550-6		51.8	<0.002	0.01	0.85	4.3	<1	0.9	27.5	0.30	<0.05	4.23	0.119	0.28	0.8
18-8550-7		52.1	<0.002	0.02	1.08	4.7	1	1.0	29.0	0.32	<0.05	4.67	0.130	0.35	0.9
18-8550-8		46.1	<0.002	0.01	1.34	4.0	<1	0.8	26.2	0.28	<0.05	4.27	0.117	0.32	0.8



ALS Canada Ltd.  
 2103 Dollarton Hwy  
 North Vancouver BC V7H 0A7  
 Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
 www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
 203 - 1634 HARVEY AVE  
 KELOWNA BC V1Y 6G2

Page: 5 - D  
 Total # Pages: 6 (A - D)  
 Plus Appendix Pages  
 Finalized Date: 12-NOV-2018  
 Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Pb-OG62 Pb % 0.001	Zn-OG62 Zn % 0.001	Au-ICP22 Au ppm 0.001
18-8548-13		0.2	10.0	189	11.2			<0.001
18-8548-14		0.2	9.0	150	8.8			0.001
18-8548-15		0.2	8.4	111	7.0			<0.001
18-8548-16		0.1	7.7	86	6.9			<0.001
18-8548-17		0.3	11.3	119	17.4			<0.001
18-8548-18		0.6	10.8	48	27.4			0.002
18-8548-19		0.7	13.1	63	36.2			0.002
18-8548-20		0.8	13.4	47	41.2			0.001
18-8548-21		0.2	1.5	<2	5.5			<0.001
18-8548-22		2.3	11.3	>10000	158.5	1.365	5.40	1.260
18-8549-1		1.0	12.0	779	74.9			0.001
18-8549-2		1.1	9.8	285	75.5			<0.001
18-8549-3		0.1	1.3	5	4.6			<0.001
18-8549-4		1.3	8.9	380	83.5			<0.001
18-8549-5		1.0	9.8	199	84.9			0.001
18-8549-6		1.5	12.4	329	92.0			0.001
18-8549-7		1.0	9.3	271	85.9			0.001
18-8549-8		1.2	8.6	237	84.4			<0.001
18-8549-9		1.1	9.2	264	88.9			<0.001
18-8549-10		1.0	9.5	661	88.8			0.001
18-8549-11		1.1	9.2	853	89.5			0.001
18-8549-12		1.4	8.6	271	89.9			<0.001
18-8549-13		1.7	8.4	196	87.6			<0.001
18-8549-14		1.3	8.7	310	80.6			<0.001
18-8549-15		1.4	10.0	1140	65.3			0.001
18-8549-16		1.2	9.7	494	83.0			0.001
18-8549-17		1.2	9.1	272	82.1			0.001
18-8549-18		1.2	15.8	43	65.7			0.003
18-8549-19		0.7	14.1	57	51.8			0.012
18-8549-20		1.0	15.7	95	58.2			0.017
18-8549-21		0.1	1.5	<2	5.4			<0.001
18-8549-22		2.5	9.8	>10000	171.5	1.375	5.24	1.255
18-8550-1		0.9	13.0	314	37.4			0.010
18-8550-2		0.9	12.3	283	34.1			0.004
18-8550-3		0.6	10.1	226	19.4			0.002
18-8550-4		0.5	10.3	88	24.1			<0.001
18-8550-5		0.5	10.8	115	25.5			0.001
18-8550-6		0.7	11.0	115	31.5			<0.001
18-8550-7		0.7	13.2	187	38.2			0.003
18-8550-8		0.7	11.8	345	30.8			<0.001



ALS Canada Ltd.  
2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 6 - A  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	WEI-21	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Recvd Wt.	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe
		kg	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.02	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1	0.05	0.2	0.01
18-8550-9		0.28	0.15	2.83	9.4	210	0.96	0.17	11.50	0.46	29.8	5.8	60	1.81	14.4	1.68
18-8550-10		0.28	0.62	3.59	10.8	270	1.20	0.22	8.59	0.49	39.9	8.2	74	2.34	21.3	2.78
18-8550-11		0.30	0.01	0.49	0.7	20	0.14	0.02	0.02	<0.02	15.10	0.8	413	0.32	4.6	0.47
18-8550-12		0.26	0.26	3.75	8.6	280	1.03	0.23	8.51	0.54	40.6	7.8	82	2.22	16.1	2.57
18-8550-13		0.28	0.40	5.20	14.6	400	1.37	0.37	2.78	0.85	56.6	12.1	121	3.19	26.7	3.70
18-8550-14		0.26	0.17	3.82	7.5	250	0.95	0.18	8.27	0.48	40.3	7.3	64	1.82	13.6	2.31
18-8550-15		0.28	0.12	4.15	5.6	280	1.12	0.16	7.51	0.25	48.5	8.4	81	2.16	13.0	2.60
18-8550-16		0.26	0.10	4.27	5.8	280	1.34	0.20	7.85	0.19	50.8	7.5	57	2.12	12.9	2.37
18-8550-17		0.32	0.10	5.00	7.7	370	1.65	0.29	4.82	0.24	57.4	11.3	94	2.62	16.6	2.99
18-8550-21		0.22	0.01	0.49	0.4	20	0.12	0.03	0.01	<0.02	16.30	0.9	407	0.31	4.2	0.51
18-8550-22		0.06	71.2	5.58	83.9	160	1.81	4.03	2.02	288	38.9	31.7	37	3.15	3700	3.69



ALS Canada Ltd.  
2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 6 - B  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P
		ppm 0.05	ppm 0.05	ppm 0.1	ppm 0.005	% 0.01	ppm 0.5	ppm 0.2	% 0.01	ppm 5	ppm 0.05	% 0.01	ppm 0.1	ppm 0.2	ppm 10
18-8550-9		7.98	0.07	1.1	0.033	1.84	14.9	27.3	7.38	1330	0.33	0.05	4.6	14.0	280
18-8550-10		9.84	0.10	1.3	0.036	2.17	18.0	32.3	5.73	1610	0.50	0.08	5.5	18.7	430
18-8550-11		1.43	0.06	0.2	<0.005	0.22	7.1	2.0	0.03	37	1.19	0.01	1.2	9.0	20
18-8550-12		9.84	0.08	1.3	0.035	2.28	18.5	32.8	5.80	1840	0.47	0.09	5.5	18.5	480
18-8550-13		14.30	0.11	1.7	0.066	2.92	25.7	46.7	2.83	2590	0.64	0.14	7.7	28.3	580
18-8550-14		10.55	0.09	1.4	0.038	2.34	18.3	35.6	5.72	1690	0.31	0.05	5.8	17.8	370
18-8550-15		11.50	0.10	1.6	0.039	2.76	22.1	31.2	5.38	1420	0.34	0.07	6.6	20.1	540
18-8550-16		12.00	0.06	1.6	0.048	2.96	23.3	33.2	5.39	1420	0.26	0.05	6.9	19.8	460
18-8550-17		12.75	0.13	1.7	0.059	3.46	29.6	42.6	3.84	1760	0.53	0.08	7.5	26.8	630
18-8550-21		1.40	0.08	0.1	0.006	0.22	7.4	2.3	0.02	38	1.24	0.01	1.2	7.5	20
18-8550-22		25.5	0.11	4.2	1.815	2.18	18.0	15.5	0.44	552	14.35	1.30	9.6	27.4	380
															>10000



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 6 - C  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
18-8550-9		65.0	<0.002	0.01	1.28	4.5	1	1.0	24.8	0.33	<0.05	4.77	0.130	0.40	0.8	26
18-8550-10		73.1	<0.002	0.02	6.43	5.7	1	1.2	26.5	0.39	<0.05	5.95	0.160	0.50	1.1	34
18-8550-11		5.4	<0.002	<0.01	0.28	0.7	<1	0.5	5.8	0.05	<0.05	2.74	0.041	0.04	0.4	6
18-8550-12		72.1	<0.002	0.02	1.29	6.1	1	1.2	27.8	0.40	<0.05	6.05	0.166	0.41	1.1	35
18-8550-13		96.8	<0.002	0.03	1.97	8.6	<1	1.7	29.6	0.56	<0.05	8.49	0.234	0.62	1.6	54
18-8550-14		73.0	<0.002	0.01	1.24	5.7	<1	1.3	22.6	0.42	<0.05	6.20	0.178	0.41	1.1	36
18-8550-15		86.9	<0.002	0.02	1.33	6.7	<1	1.5	24.8	0.49	<0.05	7.46	0.195	0.39	1.2	35
18-8550-16		93.8	<0.002	0.01	1.15	6.7	<1	1.6	23.7	0.50	<0.05	7.71	0.203	0.40	1.2	38
18-8550-17		109.5	<0.002	0.03	1.34	8.5	<1	1.6	26.4	0.55	0.05	8.35	0.228	0.48	1.3	47
18-8550-21		5.9	<0.002	<0.01	0.25	0.8	<1	0.4	6.1	0.05	<0.05	2.60	0.041	0.05	0.3	7
18-8550-22		70.9	<0.002	4.65	147.0	5.6	5	5.2	98.9	0.73	0.06	5.74	0.164	2.06	2.6	34



ALS Canada Ltd.

2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: 6 - D  
Total # Pages: 6 (A - D)  
Plus Appendix Pages  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Pb-OG62 Pb % 0.001	Zn-OG62 Zn % 0.001	Au-ICP22 Au ppm 0.001
18-8550-9		0.8	12.9	144	36.7			<0.001
18-8550-10		0.9	15.8	224	45.0			<0.001
18-8550-11		0.1	1.4	2	5.4			<0.001
18-8550-12		1.0	16.5	197	44.0			<0.001
18-8550-13		1.5	22.8	316	64.7			0.005
18-8550-14		1.1	13.7	160	46.2			0.002
18-8550-15		0.9	16.3	104	53.1			<0.001
18-8550-16		1.0	15.0	73	54.6			0.001
18-8550-17		1.0	20.6	91	62.4			0.002
18-8550-21		0.1	1.5	2	5.1			<0.001
18-8550-22		2.4	9.2	>10000	162.5	1.350	5.32	1.255



ALS Canada Ltd.  
2103 Dollarton Hwy  
North Vancouver BC V7H 0A7  
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218  
www.alsglobal.com/geochemistry

To: CANTEX MINE DEVELOPMENT CORP.  
203 - 1634 HARVEY AVE  
KELOWNA BC V1Y 6G2

Page: Appendix 1  
Total # Appendix Pages: 1  
Finalized Date: 12-NOV-2018  
Account: CANMID

Project: TA22-04-YUK8

**CERTIFICATE OF ANALYSIS VA18266880**

**CERTIFICATE COMMENTS**

**ANALYTICAL COMMENTS**

Applies to Method: REE's may not be totally soluble in this method.  
ME-MS61

**LABORATORY ADDRESSES**

Applies to Method: Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.  
Au-ICP22 LOG-24 LOG-QC ME-MS61  
ME-OG62 Pb-OG62 WEI-21 Zn-OG62