



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: **Klondike Gold Corp.**
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8 Canada

Submitted By: Notification Distribution List
Receiving Lab: Canada-Whitehorse
Received: June 25, 2019
Report Date: July 13, 2019
Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI19000079.1

CLIENT JOB INFORMATION

Project: LS
Shipment ID: KG19-17
P.O. Number
Number of Samples: 13

SAMPLE DISPOSAL

RTRN-PLP Return After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-500	12	Crush, split and pulverize 500g rock to 200 mesh			WHI
SPTRF	1	Split samples by riffle splitter			WHI
PUL85	1	Pulverize to 85% passing 200 mesh			WHI
SLBHP	0	Sort, label and box pulps			WHI
FS631	13	Metallic Sieve 500g to 150 mesh			WHI
Split +150 mesh	13	Analysis sample split/packet			WHI
Split -150	13	Analysis sample split/packet			WHI
EN002	13	Environmental disposal charge-Fire assay lead waste			VAN
FS631	13	Metallics Fire Assay for Au	30	Completed	VAN
AQ251_EXT	13	1:1:1 Aqua Regia digestion Ultratrace ICP-MS analysis	15	Completed	VAN
SHP01	13	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS

Invoice To: Klondike Gold Corp.
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8
Canada

CC: Ian Perry
Graeme Joyce
Peter Tallman
Erika Cayer



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Klondike Gold Corp.**
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8 Canada

Project: LS
Report Date: July 13, 2019

Page: 2 of 2

Part: 1 of 3

CERTIFICATE OF ANALYSIS

WHI19000079.1

	Method Analyte Unit MDL	WGHT	M150	FA430	FS600	FS600	FS600	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251
		Wgt	TotWt	-Au	TotAu	+Au	+Wt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr
		kg	g	gm/t	gm/t	gm/t	g	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm
		0.01	1	0.005	0.01	0.17	0.01	0.01	0.01	0.01	0.1	2	0.1	0.1	1	0.01	0.1	0.1	0.2	0.1	0.5
1828553	Drill Core	3.95	398	0.005	<0.01	<0.17	42.85	1.86	44.98	8.59	131.0	471	26.1	9.8	485	2.54	14.2	0.7	0.7	3.9	55.3
1828554	Drill Core	4.26	397	<0.005	<0.01	<0.17	55.06	1.42	9.49	6.83	87.4	181	17.6	11.4	409	2.83	10.0	1.0	0.2	5.5	42.5
1828555	Drill Core	5.05	394	<0.005	<0.01	<0.17	24.71	1.71	34.88	6.46	80.7	250	21.9	11.7	628	3.05	22.6	0.9	0.4	4.7	65.7
1828556	Drill Core	3.58	435	<0.005	<0.01	<0.17	45.58	1.35	23.09	11.33	78.1	215	19.5	11.3	715	2.84	16.3	0.9	0.3	3.2	83.2
1828557	Drill Core	4.77	482	0.005	<0.01	<0.17	47.40	1.28	27.83	7.44	77.5	222	17.5	11.7	692	2.75	104.0	0.8	0.9	3.9	71.9
1828558	Drill Core	2.61	415	<0.005	<0.01	<0.17	40.84	1.79	23.88	12.25	91.2	305	23.6	12.4	684	3.04	16.5	1.0	0.5	3.2	76.8
1828559	Drill Core	2.72	475	0.006	<0.01	<0.17	46.72	1.96	44.91	12.84	132.0	507	30.5	15.1	644	3.14	19.1	0.4	1.2	4.2	45.5
1828560	Core DUP		474	<0.005	<0.01	<0.17	42.54	1.97	45.64	13.24	133.9	511	31.4	15.6	660	3.21	18.9	0.5	0.8	4.3	46.5
1828561	Drill Core	3.17	443	<0.005	<0.01	<0.17	46.19	3.50	11.14	17.03	164.4	312	38.7	19.1	814	4.17	17.1	0.6	1.1	6.2	54.9
1828562	Drill Core	3.79	450	<0.005	<0.01	<0.17	43.88	1.71	17.97	26.82	126.3	342	25.6	12.1	664	3.14	12.8	0.4	0.5	4.8	46.1
1828563	Drill Core	5.58	454	0.005	<0.01	<0.17	35.20	2.16	35.75	30.82	139.8	574	33.5	14.2	692	3.41	13.5	0.6	1.3	4.6	54.8
1828564	Drill Core	5.20	405	0.006	<0.01	<0.17	50.55	2.20	43.40	13.73	99.5	490	27.9	14.8	556	2.68	20.3	1.0	1.9	4.6	41.6
1828565	Drill Core	3.71	531	0.005	<0.01	<0.17	42.75	2.04	42.31	14.44	125.3	383	29.0	15.0	711	3.04	38.5	0.6	1.2	4.4	53.1



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Klondike Gold Corp.**
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8 Canada

Project: LS
Report Date: July 13, 2019

Page: 2 of 2

Part: 2 of 3

CERTIFICATE OF ANALYSIS

WHI19000079.1

	Method Analyte Unit MDL	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	
		Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Sc	Tl	S	Hg
		ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppb
		0.01	0.02	0.02	1	0.01	0.001	0.5	0.5	0.01	0.5	0.001	1	0.01	0.001	0.01	0.1	0.1	0.02	0.02	5
1828553	Drill Core	2.51	0.63	0.06	31	0.92	0.063	7.2	26.5	1.25	136.3	0.002	1	1.42	0.004	0.20	<0.1	2.2	0.05	0.26	<5
1828554	Drill Core	0.09	0.47	0.13	30	0.52	0.068	13.9	64.0	2.03	99.7	0.004	<1	2.04	0.013	0.18	<0.1	3.0	0.04	0.03	<5
1828555	Drill Core	0.31	1.66	0.06	48	1.13	0.068	10.3	36.5	1.80	119.8	0.006	1	1.93	0.013	0.19	<0.1	4.5	0.05	0.21	<5
1828556	Drill Core	0.32	0.75	0.12	46	1.78	0.050	8.0	36.9	1.73	108.6	0.004	<1	1.84	0.012	0.18	<0.1	4.3	0.04	0.09	<5
1828557	Drill Core	0.29	2.79	0.05	39	1.87	0.056	7.8	29.2	1.58	120.5	0.003	<1	1.68	0.012	0.17	<0.1	4.0	0.04	0.20	<5
1828558	Drill Core	0.70	0.61	0.07	47	1.17	0.055	6.1	33.0	1.86	105.7	0.002	<1	1.94	0.007	0.18	<0.1	3.5	0.05	0.16	<5
1828559	Drill Core	0.54	0.55	0.12	45	0.78	0.071	7.0	40.5	1.74	117.4	0.002	<1	1.93	0.006	0.17	<0.1	2.9	0.04	0.09	<5
1828560	Core DUP	0.53	0.55	0.12	47	0.79	0.072	7.6	42.0	1.81	138.2	0.002	<1	2.01	0.007	0.20	<0.1	3.1	0.05	0.09	<5
1828561	Drill Core	0.76	0.32	0.10	47	1.30	0.099	7.9	69.1	2.58	107.7	0.003	<1	2.59	0.008	0.18	<0.1	3.2	0.04	0.04	<5
1828562	Drill Core	0.73	0.30	0.18	36	1.33	0.074	6.9	42.3	2.02	128.8	0.003	<1	2.05	0.008	0.18	<0.1	3.0	0.04	0.05	<5
1828563	Drill Core	0.92	0.88	0.25	55	0.96	0.076	7.4	45.7	2.13	110.6	0.007	<1	2.24	0.009	0.20	<0.1	4.0	0.06	0.10	<5
1828564	Drill Core	0.43	0.46	0.12	33	0.86	0.072	5.5	29.1	1.56	144.9	0.003	<1	1.70	0.006	0.22	<0.1	2.2	0.04	0.16	<5
1828565	Drill Core	0.92	0.63	0.13	36	1.09	0.077	5.7	25.5	1.71	134.9	0.003	<1	1.86	0.006	0.20	<0.1	2.5	0.04	0.15	<5



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Klondike Gold Corp.**
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8 Canada

Project: LS
Report Date: July 13, 2019

Page: 2 of 2

Part: 3 of 3

CERTIFICATE OF ANALYSIS

WHI19000079.1

	Method Analyte Unit MDL	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251
		Se	Te	Ga	Cs	Ge	Hf	Nb	Rb	Sn	Ta	Zr	Y	Ce	In	Re	Be	Li	Pd
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppb
		0.1	0.02	0.1	0.02	0.1	0.02	0.02	0.1	0.1	0.05	0.1	0.01	0.1	0.02	1	0.1	0.1	10
1828553	Drill Core	2.3	<0.02	4.3	0.52	<0.1	0.14	<0.02	7.8	0.2	<0.05	6.1	6.20	13.8	<0.02	2	0.3	21.2	<10
1828554	Drill Core	0.3	0.02	6.3	0.75	<0.1	0.12	<0.02	7.1	0.2	<0.05	5.9	7.72	27.2	<0.02	3	0.3	21.6	<10
1828555	Drill Core	1.0	0.02	6.6	1.81	<0.1	0.09	<0.02	8.1	0.2	<0.05	4.7	9.09	20.1	0.02	2	0.5	30.4	<10
1828556	Drill Core	0.5	<0.02	6.0	1.03	<0.1	0.07	<0.02	7.2	0.3	<0.05	3.6	7.07	15.5	<0.02	3	0.4	25.2	<10
1828557	Drill Core	1.2	<0.02	5.3	0.95	<0.1	0.12	<0.02	6.1	0.2	<0.05	5.9	5.82	15.0	<0.02	4	0.3	23.8	<10
1828558	Drill Core	0.9	0.03	6.2	1.28	<0.1	0.15	<0.02	8.7	0.2	<0.05	7.4	5.26	11.9	<0.02	2	0.4	40.1	<10
1828559	Drill Core	0.9	0.02	6.1	0.77	<0.1	0.19	<0.02	7.2	0.3	<0.05	10.3	5.92	13.7	<0.02	<1	0.3	32.6	<10
1828560	Core DUP	0.9	<0.02	6.3	0.72	<0.1	0.19	<0.02	8.0	0.4	<0.05	10.0	6.11	14.9	<0.02	<1	0.3	33.4	<10
1828561	Drill Core	1.3	0.05	9.5	0.62	<0.1	0.07	<0.02	7.1	0.3	<0.05	6.4	7.89	15.5	0.02	<1	0.3	34.6	<10
1828562	Drill Core	0.7	0.02	6.9	0.32	<0.1	0.23	<0.02	6.5	0.2	<0.05	11.9	5.17	13.4	<0.02	<1	0.2	23.5	<10
1828563	Drill Core	0.7	0.02	7.8	1.43	<0.1	0.19	<0.02	9.6	0.2	<0.05	9.4	7.22	14.7	<0.02	<1	0.4	30.1	<10
1828564	Drill Core	1.0	0.03	5.1	0.51	<0.1	0.14	<0.02	7.6	0.2	<0.05	7.1	4.67	10.8	<0.02	2	0.2	19.9	<10
1828565	Drill Core	1.4	0.03	5.4	0.59	<0.1	0.15	<0.02	7.4	0.2	<0.05	7.7	6.10	11.2	<0.02	1	0.3	23.9	<10



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Klondike Gold Corp.

3123-595 Burrard St.

Vancouver British Columbia V7X 1K8 Canada

Project:

LS

Report Date:

July 13, 2019

Page:

1 of 1

Part:

1 of 3

QUALITY CONTROL REPORT

WHI19000079.1

	Method	WGHT	M150	FA430	FS600	FS600	FS600	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	
	Analyte	Wgt	TotWt	-Au	TotAu	+Au	+Wt	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	
	Unit	kg	g	gm/t	gm/t	gm/t	g	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	
	MDL	0.01	1	0.005	0.01	0.17	0.01	0.01	0.01	0.01	0.1	2	0.1	0.1	1	0.01	0.1	0.1	0.2	0.1	0.5	
Pulp Duplicates																						
1828556	Drill Core	3.58	435	<0.005	<0.01	<0.17	45.58	1.35	23.09	11.33	78.1	215	19.5	11.3	715	2.84	16.3	0.9	0.3	3.2	83.2	
REP 1828556	QC							1.34	23.26	11.59	79.0	220	19.6	11.1	721	2.89	16.1	0.9	<0.2	3.2	83.4	
Reference Materials																						
STD DS11	Standard							14.19	145.60	117.15	322.9	1712	75.9	13.1	982	2.95	40.6	2.2	50.2	6.7	64.4	
STD OREAS262	Standard							0.67	116.32	49.85	141.2	460	62.5	26.6	527	3.17	34.1	1.1	64.6	8.2	34.6	
STD OXC145	Standard					0.211																
STD OXH139	Standard					1.277																
STD OXN134	Standard					7.657																
STD OXQ90	Standard						24.98	30.07														
STD OXQ90	Standard						24.88	30.03														
STD OXQ90 Expected							24.88															
STD DS11 Expected								14.6	149	138	345	1710	77.7	14.2	1055	3.1	42.8	2.59	79	7.65	67.3	
STD OREAS262 Expected								0.68	118	56	154	450	62	26.9	530	3.284	35.8	1.22	65	9.33	36	
BLK	Blank					<0.005																
BLK	Blank					<0.005																
BLK	Blank						<0.17	30.00														
BLK	Blank						<0.17	30.00														
BLK	Blank							<0.01	<0.01	<0.01	<0.1	<2	<0.1	<0.1	<1	<0.01	<0.1	<0.1	<0.2	<0.1	<0.5	
Prep Wash																						
ROCK-WHI	Prep Blank			433	<0.005	<0.01	<0.17	36.22	0.70	4.22	16.36	131.4	222	0.6	3.3	444	1.70	7.1	0.4	0.3	1.8	18.9
ROCK-WHI	Prep Blank			426	<0.005	<0.01	<0.17	39.52	0.76	2.25	5.73	42.4	74	0.7	3.3	446	1.72	1.9	0.4	<0.2	1.9	17.7



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Klondike Gold Corp.**
3123-595 Burrard St.
Vancouver British Columbia V7X 1K8 Canada

Project: LS
Report Date: July 13, 2019

Page: 1 of 1

Part: 2 of 3

QUALITY CONTROL REPORT

WHI19000079.1

	Method	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251
	Analyte	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Sc	Tl	S	Hg
	Unit	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppb
	MDL	0.01	0.02	0.02	1	0.01	0.001	0.5	0.5	0.01	0.5	0.001	1	0.01	0.001	0.01	0.1	0.1	0.02	0.02	5
Pulp Duplicates																					
1828556	Drill Core	0.32	0.75	0.12	46	1.78	0.050	8.0	36.9	1.73	108.6	0.004	<1	1.84	0.012	0.18	<0.1	4.3	0.04	0.09	<5
REP 1828556	QC	0.30	0.76	0.13	47	1.80	0.051	8.3	37.0	1.75	111.8	0.004	<1	1.84	0.011	0.18	<0.1	4.4	0.04	0.10	6
Reference Materials																					
STD DS11	Standard	2.23	8.31	9.51	47	1.02	0.064	15.9	57.2	0.81	315.6	0.088	7	1.16	0.069	0.39	2.6	3.2	4.24	0.27	209
STD OREAS262	Standard	0.57	5.66	0.85	22	2.86	0.037	15.0	43.6	1.13	221.7	0.003	4	1.45	0.064	0.31	0.2	3.3	0.43	0.25	143
STD OXC145	Standard																				
STD OXH139	Standard																				
STD OXN134	Standard																				
STD OXQ90	Standard																				
STD OXQ90	Standard																				
STD OXQ90 Expected																					
STD DS11 Expected		2.37	8.74	12.2	50	1.063	0.0701	18.6	61.5	0.85	385	0.0976		1.1795	0.0762	0.4	2.9	3.4	4.9	0.2835	260
STD OREAS262 Expected		0.61	5.06	1.03	22.5	2.98	0.04	15.9	41.7	1.17	248	0.0027	4	1.3	0.071	0.312	0.2	3.24	0.47	0.253	170
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank	<0.01	<0.02	<0.02	<1	<0.01	<0.001	<0.5	<0.5	<0.01	<0.5	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.1	<0.02	<0.02	<5
Prep Wash																					
ROCK-WHI	Prep Blank	0.51	0.76	0.08	22	0.60	0.036	4.8	2.6	0.43	39.6	0.063	3	0.81	0.063	0.07	<0.1	2.4	<0.02	0.03	<5
ROCK-WHI	Prep Blank	0.08	0.24	0.02	21	0.56	0.036	5.2	3.1	0.43	42.8	0.067	2	0.82	0.067	0.07	<0.1	2.5	<0.02	<0.02	<5



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Klondike Gold Corp.

3123-595 Burrard St.

Vancouver British Columbia V7X 1K8 Canada

Project:

LS

Report Date:

July 13, 2019

Page:

1 of 1

Part:

3 of 3

QUALITY CONTROL REPORT

WHI19000079.1

Method Analyte Unit MDL		AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251	AQ251
		Se	Te	Ga	Cs	Ge	Hf	Nb	Rb	Sn	Ta	Zr	Y	Ce	In	Re	Be	Li	Pd	Pt
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppb	ppb
		0.1	0.02	0.1	0.02	0.1	0.02	0.02	0.1	0.1	0.05	0.1	0.01	0.1	0.02	1	0.1	0.1	10	2
Pulp Duplicates																				
1828556	Drill Core	0.5	<0.02	6.0	1.03	<0.1	0.07	<0.02	7.2	0.3	<0.05	3.6	7.07	15.5	<0.02	3	0.4	25.2	<10	<2
REP 1828556	QC	0.6	0.02	6.1	1.06	<0.1	0.07	<0.02	7.2	0.3	<0.05	3.6	7.15	16.0	<0.02	3	0.4	25.3	<10	<2
Reference Materials																				
STD DS11	Standard	2.1	4.43	4.9	2.57	<0.1	0.05	1.38	33.6	1.8	<0.05	2.8	7.91	32.4	0.23	38	0.6	21.9	100	144
STD OREAS262	Standard	0.5	0.19	4.1	2.73	<0.1	0.24	<0.02	20.1	0.5	<0.05	12.1	10.93	30.4	0.03	<1	1.1	17.2	<10	<2
STD OXC145	Standard																			
STD OXH139	Standard																			
STD OXN134	Standard																			
STD OXQ90	Standard																			
STD OXQ90	Standard																			
STD OXQ90 Expected																				
STD DS11 Expected		2.2	4.56	5.1	2.88	0.08	0.06	1.53	33.6	1.8		3.1	7.82	37	0.24	50	0.67	23.3	100	172
STD OREAS262 Expected		0.4	0.23	3.73	2.8		0.27		18.6	0.5		11.7	11.2	32	0.033		1.14	17.8		
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.1	<0.02	<0.1	<0.02	<0.1	<0.02	<0.02	<0.1	<0.1	<0.05	<0.1	<0.01	<0.1	<0.02	<1	<0.1	<0.1	<10	<2
Prep Wash																				
ROCK-WHI	Prep Blank	<0.1	<0.02	3.5	0.17	<0.1	0.10	0.19	1.7	1.1	<0.05	3.0	7.73	9.7	0.08	<1	0.2	2.3	<10	<2
ROCK-WHI	Prep Blank	<0.1	<0.02	3.4	0.15	<0.1	0.11	0.19	2.0	0.4	<0.05	3.4	8.09	10.4	0.02	<1	0.2	2.0	<10	<2