

**MSALABS**

MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT: YVR2010790

Project Name: Sixtymile
Job Received Date: 13-Oct-2020
Job Report Date: 20-Jan-2021
Number of Samples: 107
Report Version: Final

COMMENTS:

Test results reported relate to the tested samples only on an "as received" basis. Unless otherwise stated above, sufficient sample was received for the methods requested and all samples were received in acceptable condition. Analytical results in unsigned reports marked "provisional" are subject to change, pending final QC review and approval. The customer has not provided any information that can affect the validity of the test results. Please refer to MSALABS' Schedule of Services and Fees for our complete Terms and Conditions. Preliminary results are applicable when a portion of samples in a job is 100% completed and reported or 1 of a number of methods on the same job have been completed 100%. Results cannot change, but additional results or results for additional methods can be added.

SAMPLE PREPARATION

METHOD CODE	DESCRIPTION
PRP-920-MET	Dry, Crush to 2mm, split 1000g sub-sample, pulverize and sieve past 106 micron mesh in order to obtain plus and minus fractions
PRP-910	Dry, Crush to 70% passing 2mm, Split 250g, Pulverize to 85% passing 75µm

ANALYTICAL METHODS

METHOD CODE	DESCRIPTION
FAS-111	Au, Fire Assay, 30g fusion, AAS, Trace Level
MSC-130	Metallic Screening 1000g, Fire Assay, 30g Fusion

Signature:

Yvette Hsi, BSc.
Laboratory Manager
MSALABS



MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT: YVR2010790

Project Name: Sixtymile
Job Received Date: 13-Oct-2020
Job Report Date: 20-Jan-2021
Report Version: Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg	Method Analyte Units	FAS-111 Au ppm	MSC-130 total g	MSC-130 (+) g	MSC-130 (-) g	MSC-130 Total Au ppm	MSC-130 Au (+) ppm	MSC-130 Au (-) ppm	MSC-130 Au (-) D ppm
		0.01	LOR	0.005	1.0	1.0	1.0	0.9	0.9	0.01	0.01
034501	Core	2.33			1007.6	20.7	986.9	<0.9	<0.9	0.02	0.02
034502	Core	2.81			997.1	19.7	977.4	<0.9	3.4	0.77	0.83
034503	Core	4.57			1003.1	24.8	978.3	<0.9	1.6	0.78	0.84
034504	Core	8.75			1062.8	28.2	1034.6	<0.9	<0.9	0.57	0.50
034505	Core	3.24			954.2	19.6	934.6	<0.9	5.7	0.84	0.63
034506	Core	4.68			1060.4	34.5	1025.9	<0.9	1.0	0.18	0.24
034507	Core	5.18			979.2	25.9	953.3	<0.9	1.5	0.49	0.48
034508	Core	8.30			981.4	27.3	954.1	<0.9	<0.9	0.10	0.08
034509	Core	7.59			990.8	26.4	964.4	<0.9	<0.9	0.08	0.07
034510	Core	7.67			978.7	24.4	954.3	<0.9	<0.9	0.06	0.05
034511	Core	2.51			1070.1	31.6	1038.5	1.2	5.2	0.92	1.28
034512	Core	4.63			1040.3	26.9	1013.4	<0.9	<0.9	0.60	0.67
034513	Core	4.88			1004.8	22.3	982.5	<0.9	6.1	0.18	0.20
034514	Core	5.13			1001.0	41.0	960.0	12.8	153.1	7.36	6.28
034515	Core	5.32			973.9	28.2	945.7	<0.9	<0.9	0.22	0.29
034516	Core	9.92			1178.7	16.8	1161.9	<0.9	4.5	0.48	0.60
034517	Core	5.34			980.6	24.4	956.2	<0.9	<0.9	0.03	0.05
034518	Core	4.85			1060.5	22.3	1038.2	<0.9	<0.9	0.16	0.08
034519	Core	4.67			1042.2	24.9	1017.3	1.1	2.3	0.97	1.24
034520	Core	4.21			1109.8	32.4	1077.4	<0.9	<0.9	0.24	0.33
034521	Core	3.26			946.6	30.3	916.3	<0.9	1.5	0.77	0.96
034522	Core	3.18			960.5	25.2	935.3	<0.9	1.1	0.33	0.40
034523	Core	2.47			1025.3	31.3	994.0	1.0	2.1	0.91	1.12
034524	Core	3.93			1064.6	26.4	1038.2	1.6	15.5	1.23	1.30
034525	Core	5.89			1056.8	24.8	1032.0	<0.9	<0.9	0.20	0.20

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT: YVR2010790

Project Name: Sixtymile
Job Received Date: 13-Oct-2020
Job Report Date: 20-Jan-2021
Report Version: Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg	Method Analyte Units	FAS-111 Au ppm	MSC-130 total g	MSC-130 (+) g	MSC-130 (-) g	MSC-130 Total Au ppm	MSC-130 Au (+) ppm	MSC-130 Au (-) ppm	MSC-130 Au (-) D ppm
		0.01	LOR	0.005	1.0	1.0	1.0	0.9	0.9	0.01	0.01
034526	Core	4.99			1119.6	33.0	1086.6	<0.9	1.2	0.20	0.23
034527	Core	4.57			1048.1	25.0	1023.1	<0.9	1.1	0.32	0.20
034528	Core	5.33			985.7	23.3	962.4	<0.9	<0.9	0.18	0.18
034529	Core	5.06			923.1	23.0	900.1	<0.9	4.5	0.10	0.11
034530	Core	3.85			887.8	23.5	864.3	<0.9	<0.9	0.35	0.17
034531	Core	5.44			984.0	28.1	955.9	<0.9	<0.9	0.29	0.36
034532	Core	5.37			978.1	30.1	948.0	<0.9	<0.9	0.20	0.27
034533	Core	4.54			1045.2	27.4	1017.8	<0.9	<0.9	0.48	0.50
034534	Core	6.00			935.9	25.4	910.5	<0.9	<0.9	0.43	0.48
034535	Core	5.26			926.1	30.4	895.7	<0.9	<0.9	0.07	0.22
034536	Core	1.33		0.218							
034537	Core	8.27			898.3	27.3	871.0	<0.9	10.1	0.29	0.26
034538	Core	1.89			931.3	27.2	904.1	<0.9	2.3	0.40	0.49
034539	Core	4.26			978.2	24.0	954.2	<0.9	3.0	0.36	0.31
034540	Core	5.22			881.0	9.1	871.9	<0.9	<0.9	0.39	0.39
034541	Core	4.64			986.5	20.1	966.4	<0.9	<0.9	0.21	0.20
034542	Core	4.88			967.4	13.5	953.9	<0.9	<0.9	0.36	0.37
034543	Core	2.96			958.3	25.0	933.3	<0.9	<0.9	0.11	0.11
034544	Core	1.72			994.4	28.3	966.1	1.1	1.3	1.10	1.08
034545	Core	3.31			1030.0	36.3	993.7	<0.9	<0.9	0.23	0.19
034546	Core	2.80			918.2	24.0	894.2	<0.9	<0.9	0.37	0.37
034547	Core	1.86			959.2	27.0	932.2	0.9	<0.9	0.94	0.90
034548	Core	3.70			987.8	28.0	959.8	1.8	1.0	1.81	1.85
034549	Core	4.43			937.9	31.5	906.4	1.1	<0.9	1.11	1.10
034550	Core	4.10			890.7	26.7	864.0	1.2	7.4	1.01	1.07

***Please refer to the cover page for comments
regarding this test report. ***



MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT: YVR2010790

Project Name: Sixtymile
Job Received Date: 13-Oct-2020
Job Report Date: 20-Jan-2021
Report Version: Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg	Method Analyte Units	FAS-111 Au ppm	MSC-130 total g	MSC-130 (+) g	MSC-130 (-) g	MSC-130 Total Au ppm	MSC-130 Au (+) ppm	MSC-130 Au (-) ppm	MSC-130 Au (-) D ppm
		0.01	LOR	0.005	1.0	1.0	1.0	0.9	0.9	0.01	0.01
034551	Core	2.44			981.7	35.7	946.0	1.1	<0.9	1.09	1.15
034552	Core	2.72			990.4	25.8	964.6	<0.9	<0.9	0.27	0.26
034553	Core	1.46			1022.0	32.2	989.8	2.1	10.4	2.05	1.56
034554	Core	3.77			949.8	16.0	933.8	<0.9	<0.9	0.81	0.73
034555	Core	3.40			926.3	31.3	895.0	<0.9	<0.9	0.35	0.27
034556	Core	4.82			1043.4	40.8	1002.6	<0.9	<0.9	0.34	0.35
034557	Core	1.93			985.7	22.0	963.7	<0.9	<0.9	0.09	0.09
034558	Core	2.66			1002.4	32.4	970.0	<0.9	<0.9	0.18	0.13
034559	Core	3.71			974.2	36.9	937.3	<0.9	<0.9	0.12	0.12
034560	Core	3.91			950.9	38.6	912.3	<0.9	<0.9	0.14	0.16
034561	Core	5.27			970.0	24.2	945.8	<0.9	<0.9	0.82	0.77
034562	Core	4.68			971.4	33.2	938.2	<0.9	<0.9	0.09	0.08
034563	Core	5.13			921.0	27.3	893.7	<0.9	<0.9	0.29	0.30
034564	Core	5.13			962.7	27.0	935.7	<0.9	8.9	0.66	0.49
034565	Core	4.31			935.6	26.0	909.6	<0.9	<0.9	0.61	0.54
034566	Core	3.53			893.4	15.5	877.9	<0.9	<0.9	0.16	0.13
034567	Core	3.54			942.7	12.5	930.2	<0.9	<0.9	0.73	0.59
034568	Core	4.70			981.9	25.5	956.4	<0.9	<0.9	0.04	0.04
034569	Core	4.06			935.6	16.0	919.6	<0.9	<0.9	0.16	0.13
034570	Core	3.90			990.6	27.0	963.6	<0.9	<0.9	0.47	0.32
034571	Core	2.99			897.9	16.1	881.8	<0.9	<0.9	0.09	0.11
034572	Core	3.25			889.6	30.6	859.0	<0.9	<0.9	0.35	0.41
034573	Core	2.93			982.6	13.0	969.6	<0.9	<0.9	0.12	0.12
034574	Core	4.67			964.1	29.1	935.0	<0.9	3.8	0.18	0.18
034575	Core	3.15			918.1	19.0	899.1	<0.9	<0.9	0.04	0.06

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT: YVR2010790

Project Name: Sixtymile
Job Received Date: 13-Oct-2020
Job Report Date: 20-Jan-2021
Report Version: Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg	Method Analyte Units	FAS-111 Au ppm	MSC-130 total g	MSC-130 (+) g	MSC-130 (-) g	MSC-130 Total Au ppm	MSC-130 Au (+) ppm	MSC-130 Au (-) ppm	MSC-130 Au (-) D ppm
		0.01	LOR	0.005	1.0	1.0	1.0	0.9	0.9	0.01	0.01
034576	Core	4.69			982.6	37.9	944.7	<0.9	<0.9	0.03	0.11
034577	Core	5.27			943.7	36.4	907.3	<0.9	<0.9	0.15	0.12
034578	Core	5.30			929.3	30.7	898.6	<0.9	<0.9	0.42	0.41
034579	Core	4.72			951.5	28.5	923.0	<0.9	<0.9	0.26	0.28
034580	Core	2.69			860.9	35.0	825.9	<0.9	<0.9	0.11	0.14
034581	Core	4.54			937.4	31.6	905.8	<0.9	<0.9	0.41	0.43
034582	Core	4.04			886.0	32.5	853.5	<0.9	1.1	0.67	0.61
034583	Core	2.87			894.0	28.5	865.5	<0.9	<0.9	0.37	0.37
034584	Core	5.08			871.6	29.2	842.4	<0.9	<0.9	0.33	0.30
034585	Core	4.47			916.9	21.7	895.2	<0.9	<0.9	0.25	0.13
034586	Core	4.25			951.7	31.9	919.8	<0.9	<0.9	0.08	0.16
034587	Core	4.45			933.9	21.5	912.4	<0.9	<0.9	0.22	0.28
034588	Core	2.32			893.1	33.4	859.7	<0.9	1.7	0.09	0.07
034589	Core	2.78			1006.4	42.1	964.3	<0.9	<0.9	0.15	0.14
034590	Core	3.05			885.6	30.3	855.3	<0.9	<0.9	0.30	0.30
034591	Core	3.27			984.0	28.8	955.2	<0.9	<0.9	0.40	0.36
034592	Core	4.00			1022.4	23.5	998.9	<0.9	<0.9	0.31	0.27
034593	Core	3.50			990.7	24.3	966.4	<0.9	<0.9	0.30	0.27
034594	Core	3.07			867.1	20.2	846.9	<0.9	<0.9	0.17	0.17
034595	Core	5.42			941.2	11.4	929.8	<0.9	<0.9	0.16	0.20
034596	Core	3.80			927.2	23.5	903.7	<0.9	<0.9	0.10	0.27
034597	Core	2.56			902.9	21.5	881.4	<0.9	<0.9	0.10	0.08
034598	Core	2.74			802.3	26.2	776.1	<0.9	<0.9	0.26	0.30
034599	Core	2.07			825.3	33.0	792.3	2.2	32.5	1.04	0.88
034600	Core	2.62			720.6	13.3	707.3	<0.9	<0.9	0.09	0.11

***Please refer to the cover page for comments
regarding this test report. ***



MSALABS
Unit 1, 20120 102nd Avenue
Langley, BC V1M 4B4
Phone: +1-604-888-0875

To: **Flow Metals Corp.**
810 - 789 West Pender Street
Vancouver, BC, V6C 1H2
Canada

TEST REPORT:

YVR2010790

Project Name:	Sixtymile
Job Received Date:	13-Oct-2020
Job Report Date:	20-Jan-2021
Report Version:	Final

Sample ID	Sample Type	PWE-100 Rec. Wt. kg 0.01	Method Analyte Units LOR	FAS-111 Au ppm 0.005	MSC-130 total g 1.0	MSC-130 (+) g 1.0	MSC-130 (-) g 1.0	MSC-130 Total Au ppm 0.9	MSC-130 Au (+) ppm 0.9	MSC-130 Au (-) ppm 0.01	MSC-130 Au (-) D ppm 0.01
034601	Core	3.97			937.4	10.5	926.9	<0.9	<0.9	0.17	0.18
034602	Core	4.49			967.0	19.5	947.5	1.7	39.4	0.96	0.94
034603	Core	1.81			884.3	12.3	872.0	<0.9	30.5	0.48	0.46
034604	Core	2.86			1047.9	21.5	1026.4	1.4	2.4	1.38	1.31
034605	Core	2.38			880.6	21.3	859.3	2.0	6.9	1.98	1.87
DDH10-02 247.45-248.53	Core	4.11			973.2	35.4	937.8	<0.9	<0.9	0.27	0.26
DDH10-03 250.01-251.46	Core	5.60			973.1	37.3	935.8	<0.9	<0.9	0.56	0.41
DUP 34536				0.367							
STD BLANK										<0.01	<0.01
STD BLANK										<0.01	<0.01
STD BLANK										<0.01	<0.01
STD BLANK									<0.9		
STD BLANK									<0.9		
STD BLANK				<0.005							
STD OxB130										0.12	0.12
STD OxF125										0.80	0.80
STD OxC129										0.20	0.20
STD OxQ115									25.1		
STD CDN-GS-20B									20.8		
STD OxQ115									25.3		
STD OxC129				0.199							

Please refer to the cover page for comments regarding this test report.